

NASA CASE NO. LAB 15526-1-SB

PRINT FIG. N/A

NOTICE

The invention disclosed in this document resulted from research in aeronautical and space activities performed under programs of the National Aeronautics and Space Administration. The invention is owned by NASA and is, therefore, available for licensing in accordance with the patent licensing regulations applicable to U.S. Government-owned inventions (37 CFR 404.1 et seq.).

To encourage commercial utilization of NASA-owned inventions, it is NASA policy to grant licenses to commercial concerns. Although NASA encourages nonexclusive licensing to promote competition and achieve the widest possible utilization, NASA will provide the necessary incentive to the licensee to achieve early practical application of the invention.

Address informational requests for this invention to the **Technology Applications Team, NASA Langley Research Center, Code 200, Hampton, Virginia 23681-0001.**

Address applications for license to the **Patent Counsel Office, Mail Stop 212, 3 Langley Boulevard, Hampton, Virginia 23681-0001.**

Serial No.: 08/689,760

Filed: 08/13/96

LaRC

POLYIMIDE FIBERS

Abstract of the Disclosure

5 A polyimide fiber having textile physical property characteristics and the process of melt extruding same from a polyimide powder. Polyimide powder formed as the reaction product of the monomers 3,4'-ODA and ODP, and endcapped with phthalic anhydride to control the molecular weight thereof, is melt extruded in the temperature range of
10 340°C to 360°C and at heights of 100.5 inches, 209 inches and 364.5 inches. The fibers obtained have a diameter in the range of 0.0068 inch to 0.0147 inch; a mean tensile strength in the range of 15.6 to 23.1 ksi; a mean modulus of 406 to 465 ksi; and a mean elongation in the range of 14 to 103%.

15

POLYIMIDE FIBERS

AWARDS ABSTRACT

A polyimide fiber and the process of forming same from a polyimide powder is disclosed. The polyimide fiber is formed by melt extruding a polyimide powder formed as the reaction product of the monomers 3,4'-ODA and ODPA, and endcapped with phthalic anhydride to control the molecular weight thereof. The polyimide fibers are melt extruded in the temperature range of 340°C to 360°C and at heights of 100.5 inches, 209 inches and 364.5 inches. The fibers obtained have a diameter in the range of 0.0068 inch to 0.0147 inch; a mean tensile strength in the range of 15.6 to 23.1 ksi; a mean modulus of 406 to 465 ksi; and a mean elongation in the range of 14 to 103%.

The novelty of the invention is the article and process of preparing polyimide fibers having textile physical property characteristics to permit use thereof in fabricating flame resistant articles ranging from clothing to aerospace components. Also, these thermoplastic fibers could be co-mingled with reinforcing media, such as glass fibers, graphite fiber, inert fibers, and the like, and subsequently melted, in-situ, to form composite structures which would have utility in fire-resistant applications in the automotive, aerospace, and other industries.

Inventors:	Terry L. St. Clair	Catharine C. Fay
Address:	17 Roberts Landing Drive Poquoson, VA 23662 SSN [REDACTED]	201 Pioneer Lane Yorktown, VA 23692 SSN [REDACTED]
Employer:	NASA LaRC	NRC Associate

Dennis C. Working
1324 Milton Street
Norfolk, VA 23505
SSN [REDACTED]
AS&M, Inc.

Initial Evaluator: Darrell R. Tenney

Serial No.: 08/689,760
Filed: 8-13-96

POLYIMIDE FIBERSCross-Reference

This application claims the benefit of U.S. Provisional Application No.
5 60/021,206, filed July 3, 1996.

Origin of the Invention

The invention described herein was jointly made by an employee of
10 the United States Government and contract employees in the performance
of work under NASA contracts. In accordance with 35 USC 202, the
contractors elected not to retain title.

Field of the Invention

15

This invention relates generally to the extrusion preparation of fibers
and relates specifically to the preparation of polyimide fibers having
enhanced flow and high mechanical properties.

20 Background of the Invention

High performance polyimides are used in the aerospace industry, for
example, in joining metals to metals, or metals to composite structures. In
addition, polyimides are rapidly finding new uses as matrix resins for
25 composites, molding powders and films. These materials display a number
of performance characteristics such as high temperature and solvent
resistance, improved flow for better wetting and bonding, high modulus,
chemical and hot water resistance, and the like. Another area of application
is in the manufacture of lighter and stronger aircraft and spacecraft

structures.

U. S. Patent No. 5,147,966 (St. Clair, et al) discloses a polyimide that can be melt processed into various useful forms such as coatings, adhesives, composite matrix resins and film. This polyimide is prepared from 3,4'-oxydianiline (3,4'-ODA) and 4,4'-oxydiphthalic anhydride (ODPA) in various organic solvents. The use of phthalic anhydride as an endcapping agent is also disclosed in this patent to control the molecular weight of the polymer and, in turn, to make it easier to process in molten form.

In the present invention, a polyimide fiber is produced from the polyimide powder that is prepared from the 3,4'-ODA and ODPA monomers. This polyimide powder was endcapped with phthalic anhydride, as described in U. S. Patent No. 5,147,966, to control the number average molecular weight in the range of 10,000 g/mole to 20,000 g/mole.

The need for polyimide fibers of this type are apparent. Since this polyimide is fire resistant, these fibers would be useful in manufacturing articles which might be exposed to flames/fire to prevent their burning. These articles would range from clothing articles to aerospace components. In addition, fibers from this polyimide, since they are thermoplastic, could be co-mingled with reinforcing media such as glass fiber, graphite fiber, inert fillers, and the like, and be subsequently melted, in-situ, to form composite structures which would have utility in fire-resistant applications in the automotive and aerospace industries.

A primary requirement for such fibers is that they have adequate textile properties to permit processing using normal textile equipment. The two primary measures of fiber quality are tensile strength and elongation-to-break percentage. Adequate strength must be developed to afford handling properties during processing and to afford adequate strength in the final form. Additionally, the fiber must possess adequate elongation-to-break

properties to provide the required toughness in the processing operations and in the final components.

Summary of the Invention

5

The invention is a polyimide fiber formed from the reaction product of 3,4'-oxydianiline (3,4'-ODA) and 4,4'-oxydiphthalic anhydride (ODPA) in 2-methoxyethyl ether (diglyme), or other suitable solvent, and endcapped with phthalic anhydride to control the number average molecular weight in
10 the range of 10,000 g/mole to 20,000 g/mole.

It is an object of the present invention to provide a polyimide fiber that has the textile physical property characteristics to permit processing into useful articles using normal textile equipment.

Another object of the present invention is polyimide fiber having high
15 strength and high elongation-to-break property characteristics.

A further object of the present invention is a process for preparing polyimide fibers via melt extrusion of a molten polyimide.

An additional object of the present invention is a process for making polyimide fibers over a range of processing conditions which produce fibers
20 having high strength and high elongation-to-break properties.

Another object of the present invention is a process for preparing polyimide fibers that exhibit mechanical properties that permits them to be used in various commercial applications.

Still another object of the present invention is to provide polyimide
25 fibers having fire resistant properties.

Description of the Preferred Embodiments

The invention and its advantages are illustrated by the specific

examples given below. Conditions for melt spinning/extrusion are detailed in the individual examples and a comparison of resulting mechanical properties are shown in the data Tables 1-3.

The polyimide powder employed in each of the specific examples was
5 the reaction product of 3,4'-ODA and 4,4'-ODPA endcapped with phthalic anhydride to control the number average molecular weight of the polymer powder in the range of 10,000 g/mole to 20,000 g/mole. This polyimide powder was obtained commercially as LaRC™-IA from IMITEC, Inc., 1990 Maxon Road, Schenectady, NY 12308.

10 In each example below, the LaRC™-IA polyimide powder, as received, was dried in an air oven at approximately 200°C for twenty-four hours prior to use to drive off any residual solvent and/or moisture. The melt extrusion was performed using a Barbender, single screw extruder, equipped with a NASA-LaRC drive unit, and provided with a 8-filament, 0.0135 inch vertical
15 die. The extrusion rate employed was 10 revolutions per minute (rpm).

Polyimide fibers were extruded from three heights to vary the diameter of the fiber: (1) 364.5 inches, (2) 209 inches, and (3) 100.5 inches. Three processing temperatures were also utilized: 340°C, 350°C and 360°C.

20 The following specific Examples are provided for purposes of illustration, and are not intended to serve as limitations of the invention.

EXAMPLES

25 Example I

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 340°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch

diameter slit and fell 30 feet, 4.5 inches (364.5 inches). The average final fiber diameter was 0.0094 inch. Mean tensile strength, modulus, and elongation were 22.7 ksi, 412 ksi, and 103%, respectively.

5 Example II

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 350°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 30 feet, 4.5 inches (364.5 inches). The average final fiber diameter was 0.0068 inch. Mean tensile strength, modulus, and elongation were 23.1 ksi, 436 ksi, and 102%, respectively.

15 Example III

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 360°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 30 feet, 4.5 inches (364.5 inches). The average fiber diameter was 0.0071. Mean tensile strength, modulus, and elongation were 20.8 ksi, 415 ksi, and 84%, respectively.

The mechanical properties of the melt-extruded fibers obtained from a height of 364.5 inches in Examples I-III are tabulated in TABLE I.

TABLE I

Processing Temperature, °C	Average Fiber Diameter, Inch	Mean Tensile Strength, ksi	Mean Modulus, ksi	Mean Elongation, %
340	0.0094	22.7	412	103
350	0.0068	23.1	436	102
360	0.0071	20.8	415	84

10 Example IV

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 340°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 17 feet, 5 inches (209 inches). The average final fiber diameter was 0.0094 inch. Mean tensile strength, modulus, and elongation were 20.9 ksi, 406 ksi, and 79%, respectively.

20 Example V

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 350°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 17 feet, 5 inches (209 inches). The average final fiber diameter was 0.0101 inch. Mean tensile strength, modulus, and elongation were 20.6 ksi, 448 ksi, and 65%, respectively.

Example VI

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 360°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 17 feet, 5 inches (209 inches). The average final fiber diameter was 0.0117 inch. Mean tensile strength, modulus, and elongation were 17.7 ksi, 441 ksi, and 34%, respectively.

The mechanical properties of the melt-extruded fibers obtained from a height of 209 inches in Examples IV-VI are tabulated in TABLE II.

TABLE II

Processing Temperature, °C	Average Fiber Diameter, Inch	Mean Tensile Strength, ksi	Mean Modulus, ksi	Mean Elongation, %
340	0.0104	20.9	406	79
350	0.0101	20.6	448	65
360	0.0117	17.7	441	34

20

Example VII

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 340°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 8 feet, 4.5 inches (100.5 inches). The average fiber diameter was 0.0147 inch. Mean tensile strength, modulus, and elongation were 19.9 ksi, 433 ksi, and 50%, respectively.

25

Example VIII

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 350°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 8 feet, 4.5 inches (100.5 inches). The average final fiber diameter was 0.0118 inch. Mean tensile strength, modulus, and elongation were 17.3 ksi, 463 ksi, and 28%, respectively.

10 Example IX

The oven dried LaRC™-IA powder was placed in the sample feed of the single screw melt extruder. The extrusion temperature was 360°C with an extrusion rate of 10 rpm. The fiber exited through the 0.0135 inch diameter slit and fell 8 feet, 4.5 inches (100.5 inches). The average final fiber diameter was 0.0115 inch. Mean tensile strength, modulus, and elongation were 15.8 ksi, 465 ksi, and 14%, respectively.

The mechanical properties of the melt-extruded fibers obtained from a height of 100.5 inches in Examples VII-IX are tabulated in TABLE III.

TABLE III

Processing Temperature, °C	Average Fiber Diameter, Inch	Mean Tensile Strength, ksi	Mean Modulus, ksi	Mean Elongation, %
340	0.0147	19.9	434	50
350	0.0118	17.3	463	28
360	0.0115	15.6	465	14

The foregoing specific Examples are given to illustrate the principal of the invention and are not intended to serve as limitations thereof.

There are many variations and modifications of the invention that will be readily apparent to those skilled in the art in the light of the above

5 teachings. It is therefore to be understood that, within the scope of the pending claims, the invention may be practiced other than as specifically described herein.

What is claimed as new and desired to be secured by Letters Patent of the United States is: