

10.00
This report has been prepared
for information and record
purposes and is not to be referenced
in any publication.

NATIONAL BUREAU OF STANDARDS REPORT

8342

Quarterly Report
on

EVALUATION OF REFRACTORY QUALITIES OF
CONCRETES FOR JET AIRCRAFT WARM-UP, POWER CHECK
MAINTENANCE APRONS, AND RUNWAYS

by

J. V. Ryan, E. C. Tuma, and W. N. Bettum



U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

THE NATIONAL BUREAU OF STANDARDS

The National Bureau of Standards is a principal focal point in the Federal Government for assuring maximum application of the physical and engineering sciences to the advancement of technology in industry and commerce. Its responsibilities include development and maintenance of the national standards of measurement, and the provisions of means for making measurements consistent with those standards; determination of physical constants and properties of materials; development of methods for testing materials, mechanisms, and structures, and making such tests as may be necessary, particularly for government agencies; cooperation in the establishment of standard practices for incorporation in codes and specifications; advisory service to government agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; assistance to industry, business, and consumers in the development and acceptance of commercial standards and simplified trade practice recommendations; administration of programs in cooperation with United States business groups and standards organizations for the development of international standards of practice; and maintenance of a clearinghouse for the collection and dissemination of scientific, technical, and engineering information. The scope of the Bureau's activities is suggested in the following listing of its four Institutes and their organizational units.

Institute for Basic Standards. Electricity. Metrology. Heat. Radiation Physics. Mechanics. Applied Mathematics. Atomic Physics. Physical Chemistry. Laboratory Astrophysics.* Radio Standards Laboratory: Radio Standards Physics; Radio Standards Engineering.** Office of Standard Reference Data.

Institute for Materials Research. Analytical Chemistry. Polymers. Metallurgy. Inorganic Materials. Reactor Radiations. Cryogenics.** Office of Standard Reference Materials.

Central Radio Propagation Laboratory.** Ionosphere Research and Propagation. Troposphere and Space Telecommunications. Radio Systems. Upper Atmosphere and Space Physics.

Institute for Applied Technology. Textiles and Apparel Technology Center. Building Research. Industrial Equipment. Information Technology. Performance Test Development. Instrumentation. Transport Systems. Office of Technical Services. Office of Weights and Measures. Office of Engineering Standards. Office of Industrial Services.

* NBS Group, Joint Institute for Laboratory Astrophysics at the University of Colorado.

** Located at Boulder, Colorado.

NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT

1002-12-10472

April 28, 1964

NBS REPORT

8342

Quarterly Report
on
EVALUATION OF REFRACTORY QUALITIES
of
CONCRETES FOR JET AIRCRAFT WARM-UP, POWER CHECK
MAINTENANCE APRONS, AND RUNWAYS
by

J. V. Ryan, E. C. Tuma and W. N. Bettum

Fire Research Section
Building Research Division

Sponsored by:

U. S. Department of the Navy
Bureau of Yards and Docks

Reference: Task Y-F015-15-102
NBS File No. 10.02/10472

IMPORTANT NOTICE

NATIONAL BUREAU OF STANDARDS
for use within the Government.
and review. For this reason, the
whole or in part, is not authorized
Bureau of Standards, Washington
the Report has been specifically

Approved for public release by the
Director of the National Institute of
Standards and Technology (NIST)
on October 9, 2015.

These accounting documents intended
be subjected to additional evaluation
the listing of this Report, either in
the Office of the Director, National
by the Government agency for which
copies for its own use.



U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

3.1 Vacuum Drying

The blast furnace slag aggregate and the Volcanite aggregate concrete specimens were removed from the vacuum chamber after 121 days at pressures below the vapor pressure of water. On the basis of measurements of electrical resistance, the specimens had reached a state of dryness equivalent to that obtained by thorough oven drying. The BF-2 specimens were broken in flexure, and compressive strength measurements were made on some of the beam ends. The results are given in Table 1. These data, plus those in NBS Reports 7878 and 8118, indicate that low pressure drying of concrete test specimens may be used, in place of oven drying, without significant effect on the strength of the concrete. However, the cited data are somewhat limited and the above conclusion should be recognized as at best tentative.

3.2 Minimal Conditioning

In an attempt to determine the combination of fog room and oven drying times required to develop both strength and jet resistance, two sets of specimens were prepared, conditioned, and tested. The first set consisted of six 12 in. diameter by 6 in. thick cylindrical specimens; the second set the same as the first plus nine 3 by 4 x 16 in. beams. The cylindrical specimens were instrumented with thermocouples at surface, 1/8 in., 1/4 in., 3/8 in., 1/2 in., and with pressure probe tubes at 1/2 in. depth. All the specimens in each set were put in the fog room as soon as the forms were stripped. At fourteen days, three cylinders, and for the second set three beams, were put in an oven heated to about 100°C. The first set (Di-4) was oven dried fourteen days, the second (Di-5) seven days. At the end of the oven drying, all six cylindrical specimens of each set were exposed to the jet impingement test. The beam specimens were broken in flexure and compressive strength measurements made on the beam ends. The results are given in Table 2.

Both sets of specimens were made of diabase aggregate concretes nominally identical to that of Di-1 described in NBS Report 7578. Additional sets will be made for other conditioning programs or with other aggregates.

Table 1. Effect of Conditioning at Vacuum (approx. vapor pressure of water) vs. Air Drying at One Atmosphere. Specimens of BF-2 Concrete.

Modulus of rupture, psi	980
Compressive strength, psi	10310
Moisture content after, percent	1.0

Table 2. Results From Specimens After Short Conditioning Periods.

	12" x 6"	Oven Dried		12" x 6"	Fog Room ^{a/}	
		Spall	Max		Spall	Max
		<u>Volume</u>	<u>Pressure</u>		<u>Volume</u>	<u>Pressure</u>
		cc	psi		cc	psi
Di-4 ^{b/}	1	0	40	2	120	162
	3	0	14	4	184	112
	5	0	0	6	200	220
	Avg	0	18	Avg	168	165
Di-5 ^{c/}	1	0	42	2	176	83
	3	0	60	4	178	20
	5	0	96	6	160	288
	Avg	0	66	Avg	171	130

^{a/} Kept in fog room until same age as duplicates oven-dried.

^{b/} Fog room to 14 days, oven dried to 28 days, tested.

^{c/} Fog room to 14 days, oven dried to 21 days, tested.

Table 3. Supplementary Tests on Specimens After Short Conditioning Periods. Di-5 Concrete.

Concretes	Modulus of Rupture, Psi		Compressive Strength, psi		Moisture Content, %	
	Avg	Max	Avg	Max	Avg	Max
Oven Dried	765	880	7950	8125	0	0
73°F/50% RH	645	700	8550	8690	4.60	4.75
Fog Room	960	1005	8830	9380	5.75	6.10





