NAT'L INST. OF STAND & TECH R.I.C.
A11104 658122
NIST PUBLICATIONS



NIST SPECIAL PUBLICATION 260-124

U.S. DEPARTMENT OF COMMERCE/Technology Administration
National Institute of Standards and Technology

Standard Reference Materials:

Standard Reference Material 1744: Aluminum Freezing-Point Standard

Gregory F. Strouse

QC
100
157
.260-124
995



The National Institute of Standards and Technology was established in 1988 by Congress to "assist industry in the development of technology . . . needed to improve product quality, to modernize manufacturing processes, to ensure product reliability . . . and to facilitate rapid commercialization . . . of products based on new scientific discoveries."

NIST, originally founded as the National Bureau of Standards in 1901, works to strengthen U.S. industry's competitiveness; advance science and engineering; and improve public health, safety, and the environment. One of the agency's basic functions is to develop, maintain, and retain custody of the national standards of measurement, and provide the means and methods for comparing standards used in science, engineering, manufacturing, commerce, industry, and education with the standards adopted or recognized by the Federal Government.

As an agency of the U.S. Commerce Department's Technology Administration, NIST conducts basic and applied research in the physical sciences and engineering, and develops measurement techniques, test methods, standards, and related services. The Institute does generic and precompetitive work on new and advanced technologies. NIST's research facilities are located at Gaithersburg, MD 20899, and at Boulder, CO 80303. Major technical operating units and their principal activities are listed below. For more information contact the Public Inquiries Desk, 301-975-3058.

Office of the Director
- Advanced Technology Program
- Quality Programs
- International and Academic Affairs

Technology Services
- Manufacturing Extension Partnership
- Standards Services
- Technology Commercialization
- Measurement Services
- Technology Evaluation and Assessment
- Information Services

Materials Science and Engineering Laboratory
- Intelligent Processing of Materials
- Ceramics
- Materials Reliability[1]
- Polymers
- Metallurgy
- Reactor Radiation

Chemical Science and Technology Laboratory
- Biotechnology
- Chemical Kinetics and Thermodynamics
- Analytical Chemical Research
- Process Measurements[2]
- Surface and Microanalysis Science
- Thermophysics[2]

Physics Laboratory
- Electron and Optical Physics
- Atomic Physics
- Molecular Physics
- Radiometric Physics
- Quantum Metrology
- Ionizing Radiation
- Time and Frequency[1]
- Quantum Physics[1]

Manufacturing Engineering Laboratory
- Precision Engineering
- Automated Production Technology
- Intelligent Systems
- Manufacturing Systems Integration
- Fabrication Technology

Electronics and Electrical Engineering Laboratory
- Microelectronics
- Law Enforcement Standards
- Electricity
- Semiconductor Electronics
- Electromagnetic Fields[1]
- Electromagnetic Technology[1]
- Optoelectronics[1]

Building and Fire Research Laboratory
- Structures
- Building Materials
- Building Environment
- Fire Safety
- Fire Science

Computer Systems Laboratory
- Office of Enterprise Integration
- Information Systems Engineering
- Systems and Software Technology
- Computer Security
- Systems and Network Architecture
- Advanced Systems

Computing and Applied Mathematics Laboratory
- Applied and Computational Mathematics[2]
- Statistical Engineering[2]
- Scientific Computing Environments[2]
- Computer Services
- Computer Systems and Communications[2]
- Information Systems

[1] At Boulder, CO 80303.
[2] Some elements at Boulder, CO 80303.

NIST Special Publication 260-124

Standard Reference Materials:

Standard Reference Material 1744: Aluminum Freezing-Point Standard

Gregory F. Strouse

Process Measurements Division
Chemical Science and Technology Laboratory
National Institute of Standards and Technology
Gaithersburg, MD 20899-0001



U.S. DEPARTMENT OF COMMERCE, Ronald H. Brown, Secretary
TECHNOLOGY ADMINISTRATION, Mary L. Good, Under Secretary for Technology
NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY, Arati Prabhakar, Director

Issued May 1995

National Institute of Standards and Technology Special Publication 260–124
Natl. Inst. Stand. Technol. Spec. Publ. 260–124, 39 pages (May 1995)
CODEN: NSPUE2

U.S. GOVERNMENT PRINTING OFFICE
WASHINGTON: 1995

For sale by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402–9325

Foreword

Since its inauguration in 1901, the National Institute of Standards and Technology (NIST), formerly the National Bureau of Standards (NBS), has issued nearly 2000 different Standard Samples or Standard Reference Materials® (SRMs). Many of these have been renewed several times; others have been replaced or discontinued as technology changed. Today, over 1000 SRMs are available, together with a large number of scientific publications related to the fundamental and applied characteristics of these materials. Each material is certified for chemical composition, chemical properties, or its physical or mechanical characteristics. Each SRM is provided with a Certificate or a Certificate of Analysis that contains the essential data concerning its properties or characteristics. The SRMs currently available cover a wide range of chemical, physical, and mechanical properties, and a corresponding wide range of measurement interests in practically all aspects of fundamental and applied science. These SRMs constitute a unique and invaluable means of transferring to the user accurate data obtained at NIST, and provide essential tools that can be used to improve accuracy in practically all areas where measurements are performed.

In addition to SRMs, the National Institute of Standards and Technology issues a variety of Reference Materials (RMs) which are sold, but not certified by NIST. They meet the ISO Guide 30-1981 (E) definition for RMs, and many meet the definition for CRMs. The documentation issued with these materials is either a: (1) "Report of Investigation," the sole authority being the author of the report. RMs are intended to further scientific or technical research on particular materials. The principal consideration in issuing RMs is to provide a homogeneous material so that investigators in different laboratories are assured that they are investigating the same material. (2) "Certificate," issued by the certifying agency (other than NIST), e.g., other national laboratories, other government agencies, other standardizing bodies, or other non-profit organizations. When deemed to be in the public interest and when alternate means of national distribution do not exist, NIST acts as the distributor for such materials.

Further information on the reference materials available from NIST may be obtained from the Standard Reference Materials Program, National Institute of Standards and Technology. Information on other NIST services may be obtained from Technology Services, National Institute of Standards and Technology, Gaithersburg, MD 20899.

In addition to these types of materials, NIST provides a number of additional services. They include: Calibration and Related Measurement Services, National Standard Reference Data system, Accreditation of Testing Laboratories, National Center for Standards and Certification Information, Weights and Measures Program and Proficiency Sample Programs.

Preface

Standard Reference Materials® (SRMs) as defined by the National Institute of Standards and Technology (NIST) are well-characterized materials, produced in quantity and certified for one or more physical or chemical properties. They are used to assure the accuracy and compatibility of measurements throughout the Nation. SRMs are widely used as primary standards in many diverse fields in science, industry, and technology, both within the United States and throughout the world. They are also used extensively in the fields of environmental and clinical analysis. In many applications, traceability of quality control and measurement processes to the national measurement system is carried out through the mechanism and use of SRMs. For many of the Nation's scientists and technologists, it is therefore of more than passing interest to know the details of the measurements made at NIST in arriving at the certified values of the SRMs produced. The NIST Special Publication 260 Series is a series of papers reserved for this purpose.

The 260 Series is dedicated to the dissemination of information on different phases of the preparation, measurement, certification, and use of NIST SRMs. In general, much more detail will be found in these papers than is generally allowed, or desirable, in scientific journal articles. This enables the user to assess the validity and accuracy of the measurement processes employed, to judge the statistical analysis, and to learn details of techniques and methods utilized for work entailing greatest care and accuracy. These papers also should provide sufficient additional information so SRMs can be utilized in new applications in diverse fields not foreseen at the time the SRM was originally issued.

Inquiries concerning the technical content of this paper should be directed to the author(s). Other questions concerned with the availability, delivery, price, and so forth, will receive prompt attention from:

Standard Reference Materials Program
Bldg. 202, Rm. 204
National Institute of Standards and Technology
Gaithersburg, MD 20899
Telephone: (301) 975-6776
FAX: (301) 948-3730

Thomas E. Gills, Chief
Standard Reference Materials Program

OTHER NIST PUBLICATIONS IN THIS SERIES

Trahey, N.M., ed., NIST Standard Reference Materials Catalog 1992-93, NIST Spec. Publ. 260 (February 1992). SN003-003-03146-1*

Michaelis, R.E., and Wyman, L.L., Standard Reference Materials: Preparation of White Cast Iron Spectro-chemical Standards, NBS Misc. Publ. 260-1 (June 1964). COM74-11061**

Michaelis, R.E., Wyman, L.L., and Flitsch, R., Standard Reference Materials: Preparation of NBS Copper-Base Spectrochemical Standards, NBS Misc. Publ. 260-2 (October 1964). COM74-11063**

Michaelis, R.E., Yakowitz, H., and Moore, G.A., Standard Reference Materials: Metallographic Char-acterization of an NBS Spectrometric Low-Alloy Steel Standard, NBS Misc. Publ. 260-3 (October 1964). COM74-11060**

Hague, J.L., Mears, T.W., and Michaelis, R.E., Standard Reference Materials: Sources of Information, Publ. 260-4 (February 1965). COM74-11059**

Alvarez, R., and Flitsch, R., Standard Reference Materials: Accuracy of Solution X-Ray Spectrometric Analysis of Copper-Base Alloys, NBS Misc. Publ. 260-5 (February 1965). PB168068**

Shultz, J.I., Standard Reference Materials: Methods for the Chemical Analysis of White Cast Iron Standards, NBS Misc. Publ. 260-6 (July 1965). COM74-11068**

Bell, R.K., Standard Reference Materials: Methods for the Chemical Analysis of NBS Copper-Base Spectro-chemical Standards, NBS Misc. Publ. 260-7 (October 1965). COM74-11067**

Richmond, M.S., Standard Reference Materials: Analysis of Uranium Concentrates at the National Bureau of Standards, NBS Misc. Publ. 260-8 (December 1965). COM74-11066**

Anspach, S.C., Cavallo, L.M., Garfinkel, S.B., et al., Standard Reference Materials: Half Lives of Mate-rials Used in the Preparation of Standard Reference Materials of Nineteen Radioactive Nuclides Issued by the National Bureau of Standards, NBS Misc. Publ. 260-9 (November 1965). COM74-11065**

Yakowitz, H., Vieth, D.L., Heinrich, K.F.J., et al., Standard Reference Materials: Homogeneity Charac-terization of NBS Spectrometric Standards II: Cartridge Brass and Low-Alloy Steel, NBS Misc. Publ. 260-10 (December 1965). COM74-11064**

Napolitano, A., and Hawkins, E.G., Standard Reference Materials: Viscosity of Standard Lead-Silica Glass, NBS Misc. Publ. 260-11** (November 1966).

Yakowitz, H., Vieth, D.L., and Michaelis, R.E., Standard Reference Materials: Homogeneity Charac-terization of NBS Spectrometric Standards III: White Cast Iron and Stainless Steel Powder Compact, NBS Misc. Publ. 260-12 (September 1966).

Spijkerman, J.J., Snediker, D.K., Ruegg, F.C., et al., Standard Reference Materials: Mossbauer Spectroscopy Standard for the Chemical Shift of Iron Compounds, NBS Misc. Publ. 260-13** (July 1967).

Menis, O., and Sterling, J.T., Standard Reference Materials: Determination of Oxygen in Ferrous Mate-rials (SRMs 1090, 1091, 1092), NBS Misc. Publ. 260-14** (September 1966).

Passaglia, E. and Shouse, P.J., Standard Reference Materials: Recommended Method of Use of Standard Ligh-Sensitive Paper for Calibrating Carbon Arcs Used in Testing Testiles for Colorfastness to Light, NBS Spec. Publ. 260-15 (July 1967). Superseded by SP 260-41.

Yakowitz, H., Michaelis, R.E., and Vieth, D.L., Standard Reference Materials: Homogeneity Charac-terization of NBS Spectrometric Standards IV: Pre-paration and Microprobe Characterization of W-20% Mo Alloy Fabricated by Powder Metallurgical Methods, NBS Spec. Publ. 260-16 (January 1969). COM74-11062**

Catanzaro, E.J., Champion, C.E., Garner, E.L., et al., Standard Reference Materials: Boric Acid; Isotopic, and Assay Standard Reference Materials, NBS Spec. Publ. 260-17 (February 1970). PB189457**

Geller, S.B., Mantek, P.A., and Cleveland, N.G., Calibration of NBS Secondary Standards Magnetic Tape Computer Amplitude Reference Amplitude Measurement "Process A", NBS Spec. Publ. 260-18 (November 1969). Superseded by SP 260-29.

Paule, R.C., and Mandel, J., Standard Reference Materials: Analysis of Interlaboratory Measurements on the Vapor Pressure of Gold (Certification of SRM 745). NBS Spec. Publ. 260-19 (January 1970). PB190071**

260-20: Unassigned

Paule, R.C., and Mandel, J., Standard Reference Materials: Analysis of Interlaboratory Measurements on the Vapor Pressures of Cadmium and Silver, NBS Spec. Publ. 260-21 (January 1971). COM74-11359**

Yakowitz, H., Fiori, C.E., and Miehaelis, R.E., Standard Reference Materials: Homogeneity Charac-terization of Fe-3 Si Alloy, NBS Spec. Publ. 260-22 (February 1971). COM74-11357**

Napolitano, A., and Hawkins, E.G., Standard Reference Materials: Viscosity of a Standard Borosilicate Glass, NBS Spec. Publ. 260-23 (December 1970). COM71-00157**

Sappenfield, K.M., Marinenko, G., and Hague, J.L., Standard Reference Materials: Comparison of Redox Standards, NBS Spec. Publ. 260-24 (January 1972). COM72-50058**

Hicho, G.E., Yakowitz, H., Rasberry, S.D., et al., Standard Reference Materials: A Standard Reference Material Containing Nominally Four Percent Austenite, NBS Spec. Publ. 260-25 (February 1971). COM74-11356**

Martin, J.F., Standard Reference Materials: NBS-U.S. Steel Corp. Joint Program for Determining Oxygen and Nitrogen in Steel, NBS Spec. Publ. 260-26 (February 1971). PB 81176620**

Garner, E.L., Machlan, L.A., and Shields, W.R., Standard Reference Materials: Uranium Isotopic Standard Reference Materials, NBS Spec. Publ. 260-27 (April 1971). COM74-11358**

Heinrich, K.F.J., Myklebust, R.L., Rasberry, S.D., et al., Standard Reference Materials: Preparation and Evaluation of SRMs 481 and 482 Gold-Silver and Gold-Copper Alloys for Microanalysis, NBS Spec. Publ. 260-28 (August 1971). COM71-50365**

Geller, S.B., Standard Reference Materials: Calibration of NBS Secondary Standard Magnetic Tape (Computer Amplitude Reference) Using the Reference Tape Amplitude Measurement "Process A-Model 2," NBS Spec. Publ. 260-29 (June 1971). COM71-50282** Supersedes Measurement System in SP 260-18.

Gorozhanina, R.S., Freedman, A.Y., and Shaievitch, A.B., (translated by M.C. Selby), Standard Reference Materials: Standard Samples Issued in the USSR (A Translation from the Russian), NBS Spec. Publ. 260-30 (June 1971). COM71-50283**

Hust, J.G., and Sparks, L.L., Standard Reference Materials: Thermal Conductivity of Electrolytic Iron SRM 734 from 4 to 300 K, NBS Spec. Publ. 260-31 (November 1971). COM71-50563**

Mavrodineanu, R., and Lazar, J.W., Standard Reference Materials: Standard Quartz Cuvettes for High Accu-racy Spectrophotometry, NBS Spec. Publ. 260-32 (December 1973). COM74-50018**

Wagner, H.L., Standard Reference Materials: Compar-ison of Original and Supplemental SRM 705, Narrow Molecular Weight Distribution Polystyrene, NBS Spec. Publ. 260-33 (May 1972). COM72-50526**

Sparks, L.L., and Hust, J.G., Standard Reference Material: Thermoelectric Voltage of Silver-28 Atomic Percent Gold Thermocouple Wire, SRM 733, Verses Common Thermocouple Materials (Between Liquid Helium and Ice Fixed Points), NBS Spec. Publ. 260-34 (April 1972). COM72-50371**

Sparks, L.L., and Hust, J.G., Standard Reference Materials: Thermal Conductivity of Austenitic Stainless Steel, SRM 735 from 5 to 280 K, NBS Spec. Publ. 260-35 (April 1972). COM72-50368**

Cali, J.P., Mandel, J., Moore, L.J., et al., Standard Reference Materials: A Reference Method for the Determination of Calcium in Serum NBS SRM 915, NBS Spec. Publ. 260-36 (May 1972). COM72-50527**

Shultz, J.I., Bell, R.K., Rains, T.C., et al., Standard Reference Materials: Methods of Analysis of NBS Clay Standards, NBS Spec. Publ. 260-37 (June 1972). COM72-50692**

Richard, J.C., and Hsia, J.J., Standard Reference Materials: Preparation and Calibration of Standards of Spectral Specular Reflectance, NBS Spec. Publ. 260-38 (May 1972). COM72-50528**

Clark, A.F., Denson, V.A., Hust, J.G., et al., Standard Reference Materials: The Eddy Current Decay Method for Resistivity Characterization of High-Purity Metals, NBS Spec. Publ. 260-39 (May 1972). COM72-50529**

McAdie, H.G., Garn, P.D., and Menis, O., Standard Reference Materials: Selection of Differential Thermal Analysis Temperature Standards Through a Cooperative Study (SRMs 758, 759, 760), NBS Spec. Publ. 260-40 (August 1972) COM72-50776**

Wood. L.A., and Shouse, P.J., Standard Reference Materials: Use of Standard Light-Sensitive Paper for Calibrating Carbon Arcs Used in Testing Textiles for Colorfastness to Light, NBS Spec. Publ. 260-41 (August 1972). COM72-50775**

Wagner, H.L., and Verdier, P.H., eds., Standard Reference Materials: The Characterization of Linear Polyethylene, SRM 1475, NBS Spec. Publ. 260-42 (September 1972). COM72-50944**

Yakowitz, H., Ruff, A.W., and Michaelis, R.E., Standard Reference Materials: Preparation and Homogeneity Characterization of an Austenitic Iron-Chromium-Nickel Alloy, NBS Spec. Publ. 260-43 (November 1972). COM73-50760**

Schooley, J.F., Soulen, R.J., Jr., and Evans, G.A., Jr., Standard Reference Materials: Preparation and Use of Superconductive Fixed Point Devices, SRM 767, NBS Spec. Publ. 260-44 (December 1972). COM73-50037**

Greifer, B., Maienthal, E.J., Rains, T.C., et al., Standard Reference Materials: Development of NBS SRM 1579 Powdered Lead-Based Paint, NBS Spec. Publ. 260-45 (March 1973). COM73-50226**

Hust, J.G., and Giarratano, P.J., Standard Reference Materials: Thermal Conductivity and Electrical Resistivity Standard Reference Materials: Austenitic Stainless Steel, SRMs 735 and 798, from 4 to 1200 K, NBS Spec. Publ. 260-46 (March 1975). COM75-10339**

Hust, J.G., Standard Reference Materials: Electrical Resistivity of Electrolytic Iron, SRM 797, and Austenitic Stainless Steel, SRM 798, from 5 to 280 K, NBS Spec. Publ. 260-47 (February 1974). COM74-50176**

Mangum, B.W., and Wise, J.A., Standard Reference Materials: Description and Use of Precision Thermo-meters for the Clinical Laboratory, SRM 933 and SRM 934, NBS Spec. Publ. 260-48 (May 1974). Superseded by NIST Spec. Publ. 260-113. COM74-50533**

Carpenter, B.S., and Reimer, G.M., Standard Reference Materials: Calibrated Glass Standards for Fission Track Use, NBS Spec. Publ. 260-49 (November 1974). COM74-51185**

Hust, J.G., and Giarratano, P.J., Standard Reference Materials: Thermal Conductivity and Electrical Resistivity Standard Reference Materials: Electrolytic Iron, SRMs 734 and 797 from 4 to 1000 K, NBS Spec. Publ. 260-50 (June 1975). COM75-10698**

Mavrodineanu, R., and Baldwin, J.R., Standard Reference Materials: Glass Filters As a SRM for Spectrophotometry-Selection, Preparation, Certification, and Use-SRM 930 NBS Spec. Publ. 260-51 (November 1975). COM75-10339**

Hust, J.G., and Giarratano, P.J., Standard Reference Materials: Thermal Conductivity and Electrical Resistivity SRMs 730 and 799, from 4 to 3000 K, NBS Spec. Publ. 260-52 (September 1975). COM75-11193**

Durst, R.A., Standard Reference Materials: Standard-ization of pH Measurements, NBS Spec. Publ. 260-53 (December 1978). Superseded by SP 260-53 Rev. 1988 Edition. PB88217427**

Burke, R.W., and Mavrodineanu, R., Standard Reference Materials: Certification and Use of Acidic Potassium Dichromate Solutions as an Ultraviolet Absorbance Standard, NBS Spec. Publ. 260-54 (August 1977). PB272168**

Ditmars, D.A., Cezairliyan, A., Ishihara, S., et al., Standard Reference Materials: Enthalpy and Heat Capacity; Molybdenum SRM 781, from 273 to 2800 K, NBS Spec. Publ. 260-55 (September 1977). PB272127**

Powell, R.L., Sparks, L.L., and Hust, J.G., Standard Reference Materials: Standard Thermocouple Material, Pt-67: SRM 1967, NBS Spec. Publ. 260-56 (February 1978). PB277172**

Cali, J.P., and Plebanski, T., Standard Reference Materials: Guide to United States Reference Materials, NBS Spec. Publ. 260-57 (February 1978). PB277173**

Barnes, J.D., and Martin, G.M., Standard Reference Materials: Polyester Film for Oxygen Gas Transmission Measurements SRM 1470, NBS Spec. Publ. 260-58 (June 1979). PB297098**

Chang, T., and Kahn, A.H., Standard Reference Materials: Electron Paramagnetic Resonance Intensity Standard: SRM 2601; Description and Use, NBS Spec. Publ. 260-59 (August 1978). PB292097**

Velapoldi, R.A., Paule, R.C., Schaffer, R., et al., Standard Reference Materials: A Reference Method for the Determination of Sodium in Serum, NBS Spec. Publ. 260-60 (August 1978). PB286944**

Verdier, P.H., and Wagner, H.L., Standard Reference Materials: The Characterization of Linear Poly-ethylene (SRMs 1482, 1483, 1484), NBS Spec. Publ. 260-61 (December 1978). PB289899**

Soulen, R.J., and Dove, R.B., Standard Reference Materials: Temperature Reference Standard for Use Below 0.5 K (SRM 768), NBS Spec. Publ. 260-62 (April 1979). PB294245**

Velapoldi, R.A., Paule, R.C., Schaffer, R., et al., Standard Reference Materials: A Reference Method for the Determination of Potassium in Serum, NBS Spec. Publ. 260-63 (May 1979). PB297207**

Velapoldi, R.A., and Mielenz, K.D., Standard Reference Materials: A Fluorescence SRM Quinine Sulfate Dihydrate (SRM 936), NBS Spec. Publ. 260-64 (January 1980). PB80132046**

Marinenko, R.B., Heinrich, K.F.J., and Ruegg, F.C., Standard Reference Materials: Micro-Homogeneity Studies of NBS SRM, NBS Research Materials, and Other Related Samples, NBS Spec. Publ. 260-65 (September 1979). PB300461**

Venable, W.H., Jr., and Eckerle, K.L., Standard Reference Materials: Didymium Glass Filters for Calibrating the Wavelength Scale of Spectrophotometers (SRMs 2009, 2010, 2013, 2014). NBS Spec. Publ. 260-66 (October 1979). PB80104961**

Velapoldi, R.A., Paule, R.C., Schaffer, R., et al., Standard Reference Materials: A Reference Method for the Determination of Chloride in Serum, NBS Spec. Publ. 260-67 (November 1979). PB80110117**

Mavrodineanu, R., and Baldwin, J.R., Standard Reference Materials: Metal-On-Quartz Filters as a SRM for Spectrophotometry SRM 2031, NBS Spec. Publ. 260-68 (April 1980). PB80197486**

Velapoldi, R.A., Paule, R.C., Schaffer, R., et al., Standard Reference Materials: A Reference Method for the Determination of Lithium in Serum, NBS Spec. Publ. 260-69 (July 1980). PB80209117**

Marinenko, R.B., Biancaniello, F., Boyer, P.A., et al., Standard Reference Materials: Preparation and Char-acterization of an Iron-Chromium-Nickel Alloy for Microanalysis: SRM 479a, NBS Spec. Publ. 260-70 (May 1981). SN003-003-02328-1*

Seward, R.W., and Mavrodineanu, R., Standard Reference Materials: Summary of the Clinical Laboratory Standards Issued by the National Bureau of Standards, NBS Spec. Publ. 260-71 (November 1981). PB82135161**

Reeder, D.J., Coxon, B., Enagonio, D., et al., Standard Reference Materials: SRM 900, Anti-epilepsy Drug Level Assay Standard, NBS Spec. Publ. 260-72 (June 1981). PB81220758

Interrante, C.G., and Hicho, G.E., Standard Reference Materials: A Standard Reference Material Containing Nominally Fifteen Percent Austenite (SRM 486), NBS Spec. Publ. 260-73 (January 1982). PB82215559**

Marinenko, R.B., Standard Reference Materials: Pre-paration and Characterization of K-411 and K-412 Mineral Glasses for Microanalysis: SRM 470, NBS Spec. Publ. 260-74 (April 1982). PB82221300**

Weidner, V.R., and Hsia, J.J., Standard Reference Materials: Preparation and Calibration of First Surface Aluminum Mirror Specular Reflectance Standards (SRM 2003a), NBS Spec. Publ. 260-75 (May 1982). PB82221367**

Hicho, G.E., and Eaton, E.E., Standard Reference Materials: A Standard Reference Material Containing Nominally Five Percent Austenite (SRM 485a), NBS Spec. Publ. 260-76 (August 1982). PB83115568**

Furukawa, G.T., Riddle, J.L., Bigge, W.G., et al., Standard Reference Materials: Application of Some Metal SRMs as Thermometric Fixed Points, NBS Spec. Publ. 260-77 (August 1982). PB83117325**

Hicho, G.E., and Eaton, E.E., Standard Reference Materials: Standard Reference Material Containing Nominally Thirty Percent Austenite (SRM 487), NBS Spec. Publ. 260-78 (September 1982). PB83115576**

Richmond, J.C., Hsia, J.J., Weidner, V.R., et al., Standard Reference Materials: Second Surface Mirror Standards of Specular Spectral Reflectance (SRMs 2023, 2024, 2025), NBS Spec. Publ. 260-79 (October 1982). PB84203447**

Schaffer, R., Mandel, J., Sun, T., et al., Standard Reference Materials: Evaluation by an ID/MS Method of the AACC Reference Method for Serum Glucose, NBS Spec. Publ. 260-80 (October 1982). PB84216894**

Burke, R.W., and Mavrodineanu, R., Standard Reference Materials: Accuracy in Analytical Spectrophoto-metry, NBS Spec. Publ. 260-81 (April 1983). PB83214536**

Weidner, V.R., Standard Reference Materials: White Opal Glass Diffuse Spectral Reflectance Standards for the Visible Spectrum (SRMs 2015 and 2016), NBS Spec. Publ. 260-82 (April 1983). PB83220723**

Bowers, G.N., Jr., Alvarez, R., Cali, J.P., et al., Standard Reference Materials: The Measurement of the Catalytic (Activity) Concentration of Seven Enzymes in NBS Human Serum (SRM 909), NBS Spec. Publ. 260-83 (June 1983). PB83239509**

Gills, T.E., Seward, R.W., Collins, R.J., et al., Standard Reference Materials: Sampling, Materials Handling, Processing, and Packaging of NBS Sulfur in Coal SRMs 2682, 2683, 2684, and 2685, NBS Spec. Publ. 260-84 (August 1983). PB84109552**

Swyt, D.A., Standard Reference Materials: A Look at Techniques for the Dimensional Calibration of Standard Microscopic Particles, NBS Spec. Publ. 260-85 (September 1983). PB84112648**

Hicho, G.E., and Eaton, E.E., Standard Reference Materials: A SRM Containing Two and One-Half Percent Austenite, SRM 488, NBS Spec. Publ. 260-86 (December 1983). PB84143296**

Mangum, B.W., Standard Reference Materials: SRM 1969: Rubidium Triple-Point - A Temperature Reference Standard Near 39.30° C, NBS Spec. Publ. 260-87 (December 1983). PB84149996**

Gladney, E.S., Burns, C.E., Perrin, D.R., et al., Standard Reference Materials: 1982 Compilation of Elemental Concentration Data for NBS Biological, Geological, and Environmental Standard Reference Materials, NBS Spec. Publ. 260-88 (March 1984). PB84218338**

Hust, J.G., Standard Reference Materials: A Fine-Grained, Isotropic Graphite for Use as NBS Thermophysical Property RMs from 5 to 2500 K, NBS Spec. Publ. 260-89 (September 1984). PB85112886**

Hust, J.G., and Lankford, A.B., Standard Reference Materials: Update of Thermal Conductivity and Electrical Resistivity of Electrolytic Iron, Tungsten, and Stainless Steel, NBS Spec. Publ. 260-90 (September 1984). PB85115814**

Goodrich, L.F., Vecchia, D.F., Pittman, E.S., et al., Standard Reference Materials: Critical Current Measurements on an NbTi Superconducting Wire SRM, NBS Spec. Publ. 260-91 (September 1984). PB85118594**

Carpenter, B.S., Standard Reference Materials: Calibrated Glass Standards for Fission Track Use (Supplement to NBS Spec. Publ. 260-49), NBS Spec. Publ. 260-92 (September 1984). PB85113025**

Ehrstein, J.R., Standard Reference Materials: Preparation and Certification of SRM for Calibration of Spreading Resistance Probes, NBS Spec. Publ. 260-93 (January 1985). PB85177921**

Gills, T.E., Koch, W.F., Stolz, J.W., et al., Standard Reference Materials: Methods and Procedures Used at the National Bureau of Standards to Certify Sulfur in Coal SRMs for Sulfur Content, Calorific Value, Ash Content, NBS Spec. Publ. 260-94 (December 1984). PB85165900**

Mulholland, G.W., Hartman, A.W., Hembree, G.G., et al., Standard Reference Materials: Development of a 1mm Diameter Particle Size Standard, SRM 1690, NBS Spec. Publ. 260-95 (May 1985). PB86113693**

Carpenter, B.S., Gramlich, J.W., Greenberg, R.R., et al., Standard Reference Materials: Uranium-235 Isotopic Abundance Standard Reference Materials for Gamma Spectrometry Measurements, NBS Spec. Publ. 260-96 (September 1986). PB87108544**

Mavrodineanu, R., and Gills, T.E., Standard Reference Materials: Summary of the Coal, Ore, Mineral, Rock, and Refactory Standards Issued by the National Bureau of Standards, NBS Spec. Publ. 260-97 (September 1985). PB86110830**

Hust, J.G., Standard Reference Materials: Glass Fiberboard SRM for Thermal Resistance, NBS Spec. Publ. 260-98 (August 1985). SN003-003-02674-3*

Callanan, J.E., Sullivan, S.A., and Vecchia, D.F., Standard Reference Materials: Feasibility Study for the Development of Standards Using Differential Scanning Calorimetry, NBS Spec. Publ. 260-99 (August 1985). PB86106747**

Taylor, J.K., Trahey, N.M., ed., Standard Reference Materials: Handbook for SRM Users, NBS Spec. Publ. 260-100 (February 1993). PB93183796**

Mangum, B.W., Standard Reference Materials: SRM 1970, Succinonitrile Triple-Point Standard: A Temperature Reference Standard Near 58.08° C, NBS Spec. Publ. 260-101 (March 1986). PB86197100**

Weidner, V.R., Mavrodineanu, R., Mielenz, K.D., et al., Standard Reference Materials: Holmium Oxide Solution Wavelength Standard from 240 to 640 nm - SRM 2034, NBS Spec. Publ. 260-102 (July 1986). PB86245727**

Hust, J.G., Standard Reference Materials: Glass Fiberblanket SRM for Thermal Resistance, NBS Spec. Publ. 260-103 (September 1985). PB86109949**

Mavrodineanu, R., and Alvarez, R., Standard Reference Materials: Summary of the Biological and Botanical Standards Issued by the National Bureau of Standards, NBS Spec. Publ. 260-104 (November 1985). PB86155561**

Mavrodineanu, R., and Rasberry, S.D., Standard Reference Materials: Summary of the Environmental Research, Analysis, and Control Standards Issued by the National Bureau of Standards, NBS Spec. Publ. 260-105 (March 1986). PB86204005**

Koch, W.F., ed., Standard Reference Materials: Methods and Procedures Used at the National Bureau of Standards to Prepare, Analyze, and Certify SRM 2694, Simulated Rainwater, and Recommendations for Use, NBS Spec. Publ. 260-106 (July 1986). PB86247483**

Hartman, A.W., and McKenzie, R.L., Standard Reference Materials: SRM 1965, Microsphere Slide (10 μm Polystyrene Spheres), NBS Spec. Publ. 260-107 (November 1988). PB89153704**

Mavrodineanu, R., and Gills, T.E., Standard Reference Materials: Summary of Gas Cylinder and Permeation Tube Standard Reference Materials Issued by the National Bureau of Standards, NBS Spec. Publ. 260-108 (May 1987). PB87209953**

Candela, G.A., Chandler-Horowitz, D., Novotny, D.B., et al., Standard Reference Materials: Preparation and Certification of an Ellipsometrically Derived Thickness and Refractive Index Standard of a Silicon Dioxide Film (SRM 2530), NIST Spec. Publ. 260-109 (October 1988). PB89133573**

Kirby, R.K., and Kanare, H.M., Standard Reference Materials: Portland Cement Chemical Composition Standards (Blending, Packaging, and Testing), NBS Spec. Publ. 260-110 (February 1988). PB88193347**

Gladney, E.S., O'Malley, B.T., Roelandts, I., et al., Standard Reference Materials: Compilation of Elemental Concentration Data for NBS Clinical, Biological, Geological, and Environmental Standard Reference Materials, NBS Spec. Publ. 260-111 (November 1987). PB88156708**

Marinenko, R.B., Blackburn, D.H., and Bodkin, J.B., Standard Reference Materials: Glasses for Micro-analysis: SRMs 1871-1875, NIST Spec. Publ. 260-112 (February 1990). PB90215807**

Mangum, B.W., and Wise, J.A., Standard Reference Materials: Description and Use of a Precision Thermometer for the Clinical Laboratory, SRM 934, NIST Spec. Publ. 260-113 (June 1990). PB90257643**

Vezzetti, C.F., Varner, R.N., and Potzick, J.E., Standard Reference Materials: Bright-Chromium Linewidth Standard, SRM 476, for Calibration of Optical Microscope Linewidth Measuring Systems, NIST Spec. Publ. 260-114 (January 1991). PB91167163**

Williamson, M.P., Willman, N.E., and Grubb, D.S., Standard Reference Materials: Calibration of NIST SRM 3201 for 0.5 in. (12.65 mm) Serial Serpentine Magnetic Tape Cartridge, NIST Spec. Publ. 260-115 (February 1991). PB91187542**

Mavrodineanu, R., Burke, R.W., Baldwin, J.R., et al., Standard Reference Materials: Glass Filters as a Standard Reference Material for Spectrophotometry -Selection, Preparation, Certification and Use of SRM 930 and SRM 1930, NIST Spec. Publ. 260-116 (March 1994). PB94-188844/AS**

Vezzetti, C.F., Varner, R.N., and Potzick, J.E., Standard Reference Materials: Anti-reflecting-Chromium Linewidth Standard, SRM 475, for Calibration of Optical Microscope Linewidth Measuring Systems, NIST Spec. Publ. 260-117 (January 1992). PB92-149798**

Williamson, M.P., Standard Reference Materials: Calibration of NIST Standard Reference Material 3202 for 18-Track, Parallel, and 36-Track, Parallel Serpentine, 12.65 mm (0.5 in), 1491 cpmm (37871 cpi), Magnetic Tape Cartridge, NIST Spec. Publ. 260-118 (July 1992). PB92-226281**

Vezzetti, C.F., Varner, R.N., and Potzick, Standard Reference Materials: Antireflecting-Chromium Linewidth Standard, SRM 473, for Calibration of Optical Microscope Linewidth Measuring System, NIST Spec. Publ. 260-119 (September 1992).

Caskey, G.W., Philips, S.D., Borchardt., et al., Standard Reference Materials: A Users' Guide to NIST SRM 2084: CMM Probe Performance Standard, NIST Spec. Publ. 260-120 (1994).

Rennex, B.G., Standard Reference Materials: Certification of a Standard Reference Material for the Determination of Interstitial Oxygen Concentration in Semiconductor Silicon by Infrared Spectrophotometry, NIST Spec. Publ. 260-121 (1994) PB95-125076/AS.

*Send order with remittance to: Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20102. Remittance from foreign countries should include an additional one fourth of the purchase price for postage.

**May be ordered from: National Technical Information Services (NTIS), Springfield, VA 22161.
For information phone (703-487-4650)
To Place an Order with PB# phone (800-553-6847)

TABLE OF CONTENTS

		PAGE
1.	Introduction	2
2.	Procedure	2
	2.1 SRM 1744 Sample	2
	2.2 Aluminum Fixed-Point Cell	2
	2.3 Assembling of the Fixed-Point Cell	4
3.	Experimental Evaluation and Analysis of Results	6
	3.1 Measurement Procedure	6
	3.2 Analysis of Freezing Curves	6
	3.3 Analysis of Melting Curves	7
	3.4 Direct Comparison of Fixed-Point Cells	14
	3.5 Application	14
4.	Conclusions	16
5.	References	17
6.	Appendix A	18

LIST OF FIGURES

FIGURE NO.		PAGE
1.	Schematic of an aluminum fixed-point cell assembly	3
2.	Freezing curves for aluminum fixed-point cell Al 94-1	8
3.	Freezing curves for aluminum fixed-point cell Al 94-2	9
4.	Freezing curves for aluminum fixed-point cell Al 94-3	10
5.	Melting curves for aluminum fixed-point cell Al 94-1	11
6.	Melting curves for aluminum fixed-point cell Al 94-2	12
7.	Melting curves for aluminum fixed-point cell Al 94-3	13
8.	Direct freezing plateau comparison results of Al 94-1, Al 94-2 and Al 94-3 with Al 78-1 (laboratory standard).	15

APPENDIX

PAGE

A. Certificate for SRM 1744: Aluminum Freezing-Point Standard. 18

Standard Reference Material 1744: Aluminum Freezing-Point Standard

Gregory F. Strouse
National Institute of Standards and Technology
Process Measurements Division
Gaithersburg, MD 20899

Abstract

The freezing point of aluminum (660.323 °C) is a defining fixed point of the International Temperature Scale of 1990 (ITS-90). Realization of this freezing point is performed using a fixed-point cell containing high-purity (≥99.9999% pure) aluminum. The aluminum constituting Standard Reference Material 1744 (SRM 1744) has been evaluated, and certified as suitable for use in the realization of the freezing-point temperature of aluminum for the ITS-90. Based on results obtained with three fixed-point cells containing random samples of SRM 1744, the plateau temperature of a freezing curve of the SRM 1744 aluminum is expected to differ by not more than 1 m°C from the ITS-90 assigned temperature. In this document, the methods used for the construction of the aluminum freezing-point cells and for the evaluation of SRM 1744 are described.

Disclaimer

Certain commercial equipment, instruments or materials are identified in this paper in order to adequately specify the experimental procedure. Such identification does not imply recommendation or endorsement by NIST, nor does it imply that the materials or equipment identified are necessarily the best available for the purpose.

Acknowledgment

The author wishes to thank the Standard Reference Materials Program for their support in the development of this new SRM and B. W. Mangum and G.T. Furukawa for their helpful discussions.

1. Introduction

One of the freezing points required to realize the International Temperature Scale of 1990 (ITS-90) from 420 °C to 962 °C is that of aluminum (660.323 °C) [1]. This freezing point is realized by using a thermometric fixed-point cell containing high-purity (≥99.9999% pure) aluminum metal. Such a fixed-point cell is used for the ITS-90 calibration of standard platinum resistance thermometers (SPRTs) from −189 °C to 660.323 °C and for high-temperature SPRTs (HTSPRTS) from 0 °C to 961.78 °C. To provide evaluated and certified material for this purpose, we have developed a Standard Reference Material (SRM), the Aluminum Freezing-Point Standard (SRM 1744).

The certification of SRM 1744 was performed by evaluating three fixed-point cells (designated Al 94-1, Al 94-2 and Al 94-3) containing random samples of the high-purity (≥99.9999% pure) metal constituting SRM 1744. The certification included the evaluation of freezing and melting curves and the direct comparison with the laboratory aluminum freezing-point standard (Al 78-1) in the NIST Platinum Resistance Thermometry (PRT) Laboratory. Using the three fixed-point cells, these methods of evaluation were used to confirm the purity and the freezing-point temperature of SRM 1744 relative to the aluminum (99.9999% pure) used in Al 78-1. The construction of the aluminum fixed-point cells used to certify SRM 1744 are described and the results from the certification of SRM 1744 are given.

2. Procedure

2.1 SRM 1744 Sample

The high-purity (≥99.9999% pure) aluminum metal used for SRM 1744 was purchased by the NIST Standard Reference Materials Program from Johnson Matthey Company of Spokane, Washington. A 20-kg lot (M2075) of high-purity aluminum metal, in millimeter size button "shot" form (nominally 0.7 cm o.d. by 0.3 cm thick) constitutes SRM 1744. Johnson Matthey Company placed the randomized metal in plastic bottles sealed in an argon atmosphere, each containing 200 g of aluminum. The purification of SRM 1744 was performed by the Johnson Matthey Company. The emission spectrographic assay provided by Johnson Matthey Company with the aluminum shows the total impurity level to be 0.4 μg/g (0.4 parts per million), resulting from 0.3 μg/g of Ca and 0.1 μg/g of Si.

2.2 Aluminum Fixed-Point Cell

Three thermometric fixed-point cells (Al 94-1, Al 94-2 and Al 94-3) were constructed to certify the aluminum metal for use as an ITS-90 freezing-point standard. Each cell contained 356 g of the high-purity metal from randomly selected bottles of lot M2075. As shown in figure 1 (schematic not drawn to scale), the aluminum (J) was contained within a high-purity graphite crucible (K) with a




Figure 1. A schematic (not to scale) of an aluminum fixed-point cell assembly showing: (A) a 25.5 Ω SPRT; (B) a matte-finished silica-glass pumping tube; (C) thermal insulation (washed Fiberfrax); (D) a matte-finished, silica-glass thermometer guide tube; (E) twelve Inconel radiation shields; (F) thirteen silica-glass spacers; (G) a silica-glass envelope with a matte-finished, silica-glass re-entrant well; (H) a graphite cap for the graphite crucible; (I) a graphite re-entrant well; (J) aluminum metal SRM 1744; (K) a graphite crucible; (L) silica-glass tape for cushioning; and (M) an Inconel protecting tube.

high-purity graphite cap (H) and a high-purity graphite re-entrant well (I). To prevent possible breakage of the cell, the graphite re-entrant well can float freely up and down (about 0.3 cm) to accommodate shrinking of the metal during freezing and some of the buoyant force of the metal experienced during melting of the metal. The graphite assembly was placed inside a silica-glass envelope (G), with a silica-glass re-entrant well (G) inserted into the graphite well. Axially located in the annular space between the graphite crucible and the silica-glass envelope was a piece of silica-glass tape (L) (46 cm long, 2.5 cm wide and 0.03 cm thick) for cushioning the graphite assembly. The silica-glass re-entrant well had a matte finish to prevent "light piping." The silica-glass envelope also had an attached silica-glass pumping tube (B) (0.6 cm o.d.) that allowed the cell to be evacuated and filled with purified argon during use. This silica-glass pumping tube had also a matte finish to prevent light piping.

The fixed-point cell was inserted into an Inconel protecting tube (M) that was 61 cm long by 5 cm o.d., with a 0.08 cm wall thickness (see fig. 1). Axially located in the annular space between the silica-glass envelope and the Inconel protecting tube and between the silica-glass envelope and the graphite crucible was a piece of silica-glass tape (each 46 cm long, 2.5 cm wide and 0.03 cm thick) for cushioning the fixed-point cell. Above the silica-glass envelope, there were 12 Inconel radiation shields (E) (4.8 cm o.d. by 0.08 cm thick) separated by 1 cm long silica-glass spacers (F), a matte-finished, silica-glass thermometer guide tube (D) and the matte-finished, silica-glass pumping tube. The first radiation shield was 2 cm above the top of the silica-glass envelope. The space remaining above the top radiation shield was filled with Fiberfrax insulation (C). Radiation shields were used to create radiation traps that temper the thermometer and help provide adequate immersion. The thermometer guide tube extended about 0.5 cm above the top of the protecting tube.

The pumping tube extended about 2.5 cm above the Inconel protecting tube and then extended about 5 cm at a right angle for connection to a vacuum/gas-handling system. This fixed-point cell assembly was placed inside a sodium-filled heat-pipe furnace for evaluation of the aluminum. A description of the sodium-filled heat-pipe furnace may be found in Refs. [2] and [3].

2.3 Assembling of the Fixed-Point Cell

Any handling procedure of high-purity material is apt to introduce contamination. The "shot" form is convenient for handling and filling during freezing-point cell construction, while a solid cylinder sample may require cutting and cleaning. By using one-time use polyethylene gloves, every possible effort was made to maintain the purity of the aluminum and other fixed-point cell components that come in contact with the aluminum. Also, a clean laboratory environment was maintained.

Prior to filling the graphite crucible with the aluminum metal "shot," the graphite crucible assembly (crucible, cap and re-entrant well) was placed in a silica-glass furnace tube and "baked-out" at 975 °C under vacuum for 4 hours. This "bake-out" of the graphite was a final purification to remove hydrocarbons and other contaminants that might have been present from the fabrication process. Additionally, the silica-glass tape used for cushioning the graphite crucible in the silica-glass envelope was inserted into the furnace tube and "baked-out" at 975 °C at a partial pressure (34 kPa) of oxygen

for 4 hours to remove any organic binders that may have been used during the manufacturing of the tape. The vacuum system used during the fabrication of the aluminum freezing-point cells is described in Ref. [4].

This silica-glass furnace tube used in the assembly process is a 4.8 cm o.d. test tube with a silica-glass pumping tube placed near the top of the furnace tube to allow for evacuation and filling with purified argon during use. The open end of the furnace tube is sealed with either a solid silicon-rubber stopper or a stopper with a vacuum seal that allows a silica-glass push rod to be used for pushing the graphite well into place.

After the graphite assembly was heated and cooled to ambient under vacuum, the furnace tube was purged with purified argon and the graphite assembly removed and placed inside a clean polyethylene bag for storage. To remove any contaminants from the "bake-out," the silica-glass furnace tube was (1) cleaned in hot, soapy water; (2) rinsed with copious amounts of water; (3) the inside soaked in 20% nitric acid-80% distilled water (volume) for 1 hour; (4) rinsed with copious amounts of distilled water and then (5) dried. After each use ("bake-out" or "fill"), the silica-glass furnace tube was cleaned.

High-purity argon gas is necessary for the during both the construction and use of the aluminum fixed-point cell. The gas purification system for argon described in Ref. [4] was designed to remove any hydrocarbons, oxygen and water that would contaminate and react with the molten aluminum.

In order to introduce 356 g of aluminum into the crucible and insert the graphite re-entrant well, two fillings were required. The aluminum "shot" was poured directly into the graphite crucible. Approximately, 290 g of aluminum "shot" could be poured into the graphite crucible for the first "fill." The graphite crucible with the graphite cap and the first filling were placed into the cleaned furnace tube and the furnace tube was placed in the furnace. The system was evacuated for 1 hour and then back-filled with purified argon to a pressure of 34 kPa. This process of pumping and flushing the system was carried out three times with the system finally under vacuum. Upon the final evacuation, the furnace was turned on and the temperature was brought to 670 °C to melt the aluminum sample. After about 2 hours the sample was completely melted, and the furnace was allowed to cool to ambient under vacuum.

For the second "fill," purified argon was introduced, the graphite crucible was removed from the furnace tube, and the remaining metal was added (about 66 g) to metal in the graphite crucible from the first "fill." The graphite re-entrant well was inserted in the graphite crucible as far as possible through the hole in the graphite cap and the assembly was placed in the newly cleaned furnace tube. A silica-glass push rod extended from the bottom of the graphite re-entrant well through a vacuum seal at the top of the furnace tube and for a sufficient distance above the seal at the top of the furnace tube to allow the graphite well to be pushed into place when the aluminum was molten. Finally, the furnace tube was placed in the furnace and pumped and flushed with purified argon using the method described above. When the sample was melted, the graphite re-entrant well was slowly inserted into the molten aluminum by pushing down the silica-glass push rod. When the graphite well was fully

inserted, the furnace was turned off and the system allowed to cool to ambient under a partial pressure (34 kPa) of purified argon. The introduction of argon during the cooling of the graphite crucible assembly was used to prevent breakage of the graphite crucible. For unknown reasons, cooling the completed graphite assembly under a vacuum may cause the graphite crucible to split. The graphite crucible assembly was ready to be placed into its silica-glass envelope and fixed-point cell assembly that was described earlier.

3. Experimental Evaluation and Analysis of Results

3.1 Measurement Procedure

The first step in evaluating the fixed-point cells was to obtain three freezing and three melting curves for each of the specimens in the cells, using a 25.5 Ω standard platinum resistance thermometer (SPRT). A commercially-available 30 Hz ac resistance ratio bridge with an ac/dc 100 Ω reference resistor was used to measure the SPRT. A description of the measurement system used in the PRT Laboratory may be found in Ref [3].

In the realization of the freezing point, the recommended "induced inner freeze" method [5, 6] was used. With the metal completely melted, the furnace was set at about 2 °C below the freezing-point temperature. After supercooling and recalescence were observed with a 25.5 Ω SPRT in the fixed-point cell, the furnace temperature was set to about 1 °C below the freezing-point temperature for the duration of the freeze. Next, the thermometer was removed and a silica-glass rod was twice successively inserted into and removed from the thermometer well at 1 minute intervals to induce freezing of a mantle of metal around the graphite re-entrant well. Finally, the thermometer was then reinserted into the cell and, after equilibrium was obtained, the recording of readings was started, using an excitation current of 1 mA.

3.2 Analysis of Freezing Curves

Figures 2 to 4 show the freezing curves for each of the three fixed-point cells (the region of supercooling and recalescence is not shown, as the curves begin after the reinsertion of the thermometer). Using an excitation current of 1 mA, thermometer readings were recorded continuously until the freezing was complete. The average length of a freeze for the three cells was 16 hours. The calculated temperature depression when 50% of the metal was frozen and the shapes from the freezing-curve plateaus were used to estimate and confirm the overall purity of the sample in the cell.

In most cases, including the two known impurities in the present high-purity samples will cause a depression in the temperature of a freezing point. Using Raoult's Law of dilute solutions, calculations may be made to estimate the expected temperature depression when 50% of the metal has frozen during a freezing curve realization [7]. Using the known type and amount of impurities given in the emission spectrographic assay, the molar fraction of impurities was calculated. The total impurity

level (2.98 X 10^{-7} mol) and Raoult's Law of dilute solutions give a calculated depression in temperature estimated to be 0.2 m°C. Another method of estimating the expected temperature depression when 50% of the metal has frozen during a freezing curve realization, was made using binary phase diagrams [8]. The binary phase diagrams for Al-Ca and Al-Si give a calculated depression in temperature estimated to be 0.3 m°C. As determined from the freezing curve plateaus in figures 2 to 4, the average estimated temperature depression from the extrapolated 0% frozen metal (time of recalescence) to the 50% frozen metal of the flat section of the plateaus were 0.6 m°C, 0.5 m°C and 0.6 m°C for Al 94-1, Al 94-2 and Al 94-3, respectively, which are several times larger than the calculated values. Differences between the calculated and the experimentally derived temperature depressions may indicate either an uncertainty in using Raoult's Law of dilute solutions, in using binary phase diagrams, the sample contained additional impurities not accounted for in the emission spectrographic assay or perhaps additional impurities were added to the metal during the construction of the fixed-point cells. In estimating the expected temperature depression, Raoult's Law of dilute solutions and binary phase diagrams are intended to provide a guideline and should not be strictly applied. Additionally, there is an uncertainty in the extrapolation method chosen to experimentally derive the temperature depression.

Comparisons of the average temperature depressions when 50% of the metal of the three fixed-point cells was frozen were made with Al 78-1. The average temperature depression from the extrapolated 0% frozen metal (time of recalescence) to the 50% frozen metal of the flat section of the plateaus was 0.7 m°C for Al 78-1. The smaller temperature depressions for the three cells relative to the laboratory standard indicate that the SRM metal is of slightly higher purity than that of the reference cell.

3.3 Analysis of Melting Curves

After the aluminum was slowly and completely frozen in the above manner, the furnace temperature was set at about 1 °C above the freezing-point temperature to slowly melt the metal over a time of approximately 10 hours. Using an excitation current of 1 mA, thermometer readings were recorded continuously until the melting was complete. Figures 5 to 7 show the melting curves for each of the three fixed-point cells. From the graphs, the average temperature range of the melting curves were 1.4 m°C, 1.0 m°C and 1.2 m°C for Al 94-1, Al 94-2 and Al 94-3, respectively.

During the melting of the aluminum, two liquid-solid interfaces are formed. One liquid-solid interface is next to the inner wall of the graphite crucible and the second liquid-solid interface is near the graphite re-entrant well. This second liquid-solid interface is formed where the lower-purity metal solidified at the end of the previous slow freeze. The lower-purity metal has a slightly lower freezing and melting temperature causing this second liquid-solid interface to form during the melt. The height of the freezing range and the melting range are about the same which is expected if an inner melt is formed during the melt [9].




Figure 2. Three freezing curves for the aluminum fixed-point cell Al 94-1 using the "induced inner freeze" preparation technique.




Figure 3. Three freezing curves for the aluminum fixed-point cell Al 94-2 using the "induced inner freeze" preparation technique.




Figure 4. Three freezing curves for the aluminum fixed-point cell Al 94-3 using the "induced inner freeze" preparation technique.




Figure 5. Three melting curves for the aluminum fixed-point cell Al 94-1 following a slow freeze. Each melt followed the respective slow freeze of Figure 2.




Figure 6. Three melting curves for the aluminum fixed-point cell Al 94-2 following a slow freeze. Each melt followed the respective slow freeze of Figure 3.




Figure 7. Three melting curves for the aluminum fixed-point cell Al 94-3 following a slow freeze. Each melt followed the respective slow freeze of Figure 4.

The temperature range of a melting curve is not indicative of the purity of the metal. Using the melting curve to indicate purity is complicated by the fact that the shape and range of a melting curve will depend upon the history of the previous freezing of the metal in the fixed-point cell [10]. A slow freeze causes the impurities to be segregated which in turn causes a large melting range. A fast freeze causes a homogenous mixture of the impurities with metal sample which in turn causes a small melting range.

3.4 Direct Comparison of Fixed-Point Cells

The second part of the evaluation was a direct comparison of the fixed-point cells under test with the laboratory standard fixed-point cell (Al 78-1) to determine their freezing-point temperatures relative to that of the reference cell. This was obtained by realizing simultaneous freezes for the two cells (Al 94-X and Al 78-1, where X was 1, 2 or 3) and making three sets of alternate measurements, at equal time intervals, on their freezing-curve plateaus, using an SPRT. Measurements of each cell were made using an SPRT with excitation currents of 1 mA and 1.414 mA to permit extrapolation to zero-power dissipation (0 mA). Corrections were made for any differences in pressure and hydrostatic head effects in each cell. Each cell was measured using an SPRT three times during the direct comparison and this procedure was repeated two times. Figure 8 shows the results of the direct comparison of the three SRM cells with the laboratory standard. The set of matching symbols (open and closed) are for the direct comparison measurements of Al 94-X (where X is 1, 2 or 3) compared with Al 78-1. Each set of symbols (open or closed) connected by lines are for the direct comparison measurements made during the simultaneous freezes. The average temperature difference of the first readings of each direct comparison showed that Al 94-1, Al 94-2 and Al 94-3 were 0.1_9 m°C, 0.3_2 m°C and 0.1_5 m°C hotter than the laboratory standard. An expanded uncertainty of 1.0 m°C (k=2) is assigned to the laboratory reference cell. The basis for that uncertainty is given in Refs. [11] and [12].

For the metal to be certified as a freezing-point standard, the fixed-point cells containing samples of the metal must have a freezing-point temperature that is in agreement with the laboratory reference cell containing high-purity metal to within the uncertainties of the measurements. If the purity of the metal in the new fixed-point cell is greater than that of the reference cell, then it may be of even higher quality, as indicated by being "hotter" than the laboratory standard. A cell that is "hotter" usually has fewer impurities, since impurities in these samples will usually decrease the freezing-point temperature.

3.5 Application

In assigning a temperature value to realizations of the aluminum freezing point, corrections must be applied for the depth of immersion (ℓ) of the thermometer sensing element below the surface of the metal ($dt/d\ell = 1.6 \times 10^{-3}$ °C/m) [1]. Also, if the pressure (p) over the cell during the measurements is not controlled at 101 325 Pa (1 standard atmosphere), a correction ($dt/dp = 7.0 \times 10^{-8}$ °C/Pa) must




Figure 8. Direct freezing plateau comparison results of Al 94-1, Al 94-2 and Al 94-3 with Al 78-1 (laboratory standard). The differences shown in the legend represent the average temperature difference from the first readings of each direct comparison. The set of matching symbols (open and closed) are for the direct comparison measurements of Al 94-X (where X is 1, 2 or 3) compared with Al 78-1. Each set of symbols (open or closed) connected by lines are for the direct comparison measurements made during the simultaneous freezes.

be made for the difference in pressure [1]. The immersion depth for the three cells was 18 cm from the sensor mid-point of the SPRT to the top of the liquid metal surface (distance from the bottom of the graphite re-entrant well to the top of the liquid level is 20.5 cm). The pressure in the cells during use was 101 325 Pa ±27 Pa.

For those constructing their own aluminum freezing-point cell containing SRM 1744, it is necessary to confirm that the purity of the metal was maintained during construction of that cell. This confirmation is made by comparing the freezing and melting curves of the new cell with those shown in figures 2-7. As a continuing check on the overall purity of the aluminum metal contained in the fixed-point cell, melting and freezing curves should be obtained every 6 months and compared with those obtained previously.

4. Conclusions

The evaluation of SRM 1744 for use as an aluminum freezing-point standard has shown that the material is of high-purity (≥99.9999%) and is acceptable for use as a defining fixed point of the ITS-90 and has been so certified. Based on the results from the evaluation of the three fixed-point cells containing SRM 1744, the average temperature range of melting of the bulk material is not expected to exceed 1.5 m°C. Plateau temperatures of the freezing curves for this material are expected to differ by not more than 0.5 m°C from each other. The results from the evaluation of the three fixed-point cells using freezing and melting curves and direct comparisons of the freezing-point temperature with that of the laboratory standard (Al 78-1) indicates that the plateau temperature of a freezing curve of the SRM 1744 aluminum is expected to differ by not more than 1 m°C from the ITS-90 assigned temperature. A copy of the certificate for SRM 1744 is given in the appendix.

Direct comparisons of the three fixed-point cells (Al 94-1, Al 94-2 and Al 94-3) with the laboratory standard (Al 78-1) have shown that the aluminum of SRM 1744 is of slightly higher purity than any samples of aluminum previously obtained by us. Consequently, fixed-point cell Al 94-2 has been selected to be the new laboratory standard at NIST for the ITS-90 realization of the freezing point of aluminum. Of the three cells, Al 94-2 has the smallest freezing-curve temperature depression, smallest melting-curve temperature range and has the "hottest" freezing-point temperature relative to the old laboratory standard (Al 78-1). The other two fixed-point cells (Al 94-1 and Al 94-3), however, are also acceptable for use as laboratory standards and they will be kept in reserve for that purpose and for control checks of the laboratory standard Al 94-2.

5. References

[1] H. Preston-Thomas, "The International Temperature Scale of 1990 (ITS-90)," *Metrologia*, Vol. 27, pp. 3-10, (1990); *ibid.* p. 107.

[2] J.P. Evans, "Evaluation of Some High-Temperature Platinum Resistance Thermometers," J. Res. Natl. Bur. Stands. (U.S.), **89**, No. 5, pp. 349-373 (1984).

[3] G.F. Strouse, "NIST Implementation and Realization of the ITS-90 Over the Range 83 K to 1235 K. Reproducibility, Stability, and Uncertainties," *Temperature. Its Measurement and Control in Science and Industry*, Edited by J.F. Schooley, Vol. 6, pp. 169-174, (American Institute of Physics, New York, 1992).

[4] G.T. Furukawa, J.L Riddle, W.R. Bigge and E.R. Pfeiffer, "Application of Some Metal SRM's as Thermometric Fixed Points," NBS SP260-77, 140 pp. (1982).

[5] E.H. McLaren, "The Freezing Points of High Purity Metals as Precision Temperature Standards," Canadian J. of Phys., **35**, pp. 1086-1106 (1957).

[6] B.W. Mangum and G.T. Furukawa, "Guidelines for Realizing the International Temperature Scale of 1990 (ITS-90)," NIST Technical Note 1265, 190 pp. (1990).

[7] S. Glasstone, *Thermodynamics for Chemists*, p. 322, (D. Van Nostrand Co., Inc., New York, 1947).

[8] *Binary Alloy Phase Diagrams*, Editor-in-Chief T.B. Massalski, Vol. 1, (ASM International, 1990).

[9] Private communication with G.T. Furukawa.

[10] J.V. McAllan and M.M. Ammar, "Comparison of the Freezing Points of Aluminum and Antimony," *Temperature. Its Measurement and Control in Science and Industry*, Edited by H.H. Plumb, Vol. 4, pp. 275-285, (Instrument Society of America, Pittsburgh, 1972).

[11] B.N. Taylor and C.E. Kuyatt, "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Results," NIST Technical Note 1297, 17 pp. (1993).

[12] G.F. Strouse and W.L. Tew, "Assessment of Uncertainties of Calibration of Resistance Thermometers at the National Institute of Standards and Technology," NISTIR 5319, 16 pp. (1994).

6. Appendix A

Certificate for SRM 1744: Aluminum Freezing-Point Standard.

National Institute of Standards & Technology

Certificate of Analysis

Standard Reference Material 1744

Aluminum Freezing-Point Standard

660.323 °C
International Temperature Scale of 1990 (ITS-90)

The certified value of 660.323 °C is the temperature assigned to the freezing-point of pure aluminum as one of the defining fixed points of the International Temperature Scale of 1990 (ITS-90) [1]. The fixed point is realized as the plateau temperature (or liquidus point) of the freezing curve of slowly-frozen high-purity aluminum. The metal is in the form of millimeter-size "shot" and is packaged in 200 g units in plastic bottles in the presence of argon.

Certified Freezing-Point Temperature: 660.323 ± 0.001 °C

Based on samples tested, the temperature range of melting of the bulk material is not expected to exceed 0.0015 °C. Temperatures of freezing curve plateau (see Figure 2) for samples of this material are expected to differ by not more than 0.0005 °C from each other and by not more than 0.001 °C from the assigned temperature. The expanded uncertainty (k=2), gives a 95.45% level of confidence for the fixed point measurements and is described in detail in reference 2.

The aluminum for this Standard Reference Material (SRM) is of high-purity, with the total of all elements that affect the freezing-point temperature being less than one mg/kg (part per million).

Source of Material: The aluminum metal (Lot M2075) for this SRM was obtained from Johnson Matthey Co., Spokane, WA 99216.

Notice and Warnings to Users: Any handling procedure for high-purity material is apt to introduce contamination. The "shot" form of this SRM minimizes the need for handling during freezing-point cell construction. Nevertheless, every possible effort should be made to maintain the purity of this SRM through the use of polyethylene gloves during handling. Also, a clean laboratory environment is essential.

In assigning a temperature value to realizations of the aluminum freezing-point for calibration purposes, corrections must be applied for the average depth of immersion (ℓ) of the thermometer sensing element below the surface of the metal ($dt/d\ell = 1.6 \times 10^{-3}$ °C/m). Also, if the pressure (p) over the cell during the measurements is not controlled at 1 standard atmosphere (101325 Pa), a correction ($dt/dp = 7.0 \times 10^{-8}$ °C/Pa) must be made for the difference in pressure.

Temperature studies on freezing-point cells prepared using metal from randomly-selected bottles were performed by G.F. Strouse of the NIST Process Measurements Division.

The technical and support aspects involved in the preparation, certification, and issuance of this SRM were coordinated through the Standard Reference Materials Program by J.C. Colbert.

Gaithersburg, MD 20899
November 4, 1994

Thomas E. Gills, Chief
Standard Reference Materials Program

(over)

Certification Testing: The thermal tests for the certification of this SRM were performed on three freezing-point cells prepared in a manner similar to that described in reference 3 listed below. Each cell contained approximately 356 g of aluminum obtained from randomly-selected bottles of the lot.

The freezing-point temperature was determined using the recommended "induced inner freeze" method [4]. With the metal completely melted, the furnace temperature was set at about 2 °C below the freezing-point temperature. After supercooling and recalescence had been observed with a 25.5 Ω standard platinum resistance thermometer (SPRT) in the cell, the thermometer was removed and a silica-glass rod was twice successively inserted into and removed from the thermometer well at one min intervals to induce freezing of a mantle of metal around the well. The thermometer was then reinserted into the cell and, after equilibrium was obtained, recording of readings was begun. After equilibrium was established, the measured temperatures of the plateaux of the nine freezing curves of the three samples decreased by no more than 0.0007 °C during the first 50 percent of the freezing curves. A typical freezing curve obtained under such conditions is shown in Figure 1 (the region of supercooling and recalescence is not shown, as the curve begins after the reinsertion of the thermometer); some of the same data are plotted at greater resolution in Figure 2.

After the metal was slowly and completely frozen in the above manner, the furnace temperature was set at about 2 °C above the freezing-point temperature to slowly melt the metal over a time of approximately 10 h. Thermometer readings were recorded continuously until the melting was complete. A typical melting curve obtained under such conditions is shown in Figure 3; some of the same data are plotted at greater resolution in Figure 4.

During the freezing and melting curve measurements, an environment of argon gas at one standard atmosphere (101325 Pa) pressure was maintained in the cells.

Following the freezing and melting curve measurements, the plateau temperature of a freezing curve of each test cell was compared directly with that of the standard aluminum freezing-point cell of the Platinum Resistance Thermometer Calibration Laboratory, using a 25.5 Ω SPRT.

REFERENCES

[1] Preston-Thomas, H., "The International Temperature Scale of 1990 (ITS-90)," Metrologia **27**, 3-10 (1990), Metrologia **27**, 107, 1990.

[2] Strouse, G.F. and Tew, W.L., "Assessment of Uncertainties of Calibration of Resistance Thermometers at the National Institute of Standards and Technology," NISTIR 5319, 16 pages, 1994.

[3] Furukawa, G.T., Riddle, J.L., Bigge, W.R., and Pfeiffer, E.R., "Standard Reference Materials: Application of Some Metal SRM's as Thermometric Fixed Points," Natl. Bur. Stand. (U.S.), Spec. Publ. 260-77, 140 pages, 1982,.

[4] Mangum, B.W. and Furukawa, G.T., "Guidelines for Realizing the International Temperature of 1990 (ITS-90)," Natl. Inst. Stand. Tech. Tech. Note 1265, 190 pages, 1990.




Figure 1. A freezing curve of SRM 1744 aluminum using the "induced-inner-freeze" preparation technique.




Figure 2. The freezing plateau region of Figure 1 at greater resolution.




Figure 3. A melting curve of SRM 1744 aluminum following a slow freeze. This melt followed the slow freeze of Figure 1.




Figure 4. The melting plateau region of Figure 3 at greater resolution.

NIST Technical Publications

Periodical

Journal of Research of the National Institute of Standards and Technology—Reports NIST research and development in those disciplines of the physical and engineering sciences in which the Institute is active. These include physics, chemistry, engineering, mathematics, and computer sciences. Papers cover a broad range of subjects, with major emphasis on measurement methodology and the basic technology underlying standardization. Also included from time to time are survey articles on topics closely related to the Institute's technical and scientific programs. Issued six times a year.

Nonperiodicals

Monographs—Major contributions to the technical literature on various subjects related to the Institute's scientific and technical activities.

Handbooks—Recommended codes of engineering and industrial practice (including safety codes) developed in cooperation with interested industries, professional organizations, and regulatory bodies.

Special Publications—Include proceedings of conferences sponsored by NIST, NIST annual reports, and other special publications appropriate to this grouping such as wall charts, pocket cards, and bibliographies.

National Standard Reference Data Series—Provides quantitative data on the physical and chemical properties of materials, compiled from the world's literature and critically evaluated. Developed under a worldwide program coordinated by NIST under the authority of the National Standard Data Act (Public Law 90-396). NOTE: The Journal of Physical and Chemical Reference Data (JPCRD) is published bimonthly for NIST by the American Chemical Society (ACS) and the American Institute of Physics (AIP). Subscriptions, reprints, and supplements are available from ACS, 1155 Sixteenth St., NW, Washington, DC 20056.

Building Science Series—Disseminates technical information developed at the Institute on building materials, components, systems, and whole structures. The series presents research results, test methods, and performance criteria related to the structural and environmental functions and the durability and safety characteristics of building elements and systems.

Technical Notes—Studies or reports which are complete in themselves but restrictive in their treatment of a subject. Analogous to monographs but not so comprehensive in scope or definitive in treatment of the subject area. Often serve as a vehicle for final reports of work performed at NIST under the sponsorship of other government agencies.

Voluntary Product Standards—Developed under procedures published by the Department of Commerce in Part 10, Title 15, of the Code of Federal Regulations. The standards establish nationally recognized requirements for products, and provide all concerned interests with a basis for common understanding of the characteristics of the products. NIST administers this program in support of the efforts of private-sector standardizing organizations.

Order the **following** *NIST publications—FIPS and NISTIRs—from the National Technical Information Service, Springfield, VA 22161.*

Federal Information Processing Standards Publications (FIPS PUB)—Publications in this series collectively constitute the Federal Information Processing Standards Register. The Register serves as the official source of information in the Federal Government regarding standards issued by NIST pursuant to the Federal Property and Administrative Services Act of 1949 as amended, Public Law 89-306 (79 Stat. 1127), and as implemented by Executive Order 11717 (38 FR 12315, dated May 11, 1973) and Part 6 of Title 15 CFR (Code of Federal Regulations).

NIST Interagency Reports (NISTIR)—A special series of interim or final reports on work performed by NIST for outside sponsors (both government and nongovernment). In general, initial distribution is handled by the sponsor; public distribution is by the National Technical Information Service, Springfield, VA 22161, in paper copy or microfiche form.

U.S. Department of Commerce
National Institute of Standards and Technology
Gaithersburg, MD 20899-0001

Official Business
Penalty for Private Use $300