


Reference

NBS
Publi-
cations

A11101 729178

NAT'L INST. OF STAND & TECH




A11107 385794

CONTAINER BOARD

NBSIR 80-1829

report no. 125
February 1980



NBS Collaborative Reference
Program for Containerboard

Fourdrinier Kraft Board Group
American Paper Institute, Inc.
and U.S. Department of
Commerce, National Bureau
of Standards

QC

100

.U56

80-1829

1980

NBS COLLABORATIVE REFERENCE PROGRAMS

TAPPI Paper and Board (6 times per year)

Bursting strength	Smoothness
Tearing strength	Surface pick strength
Tensile breaking strength	K & N ink absorption
Elongation to break	Moisture content
Tensile energy absorption	Opacity
Folding endurance	Blue reflectance (brightness)
Stiffness	Specular gloss, 75°
Air resistance	Thickness
Grammage	Concora (flat crush)
	Ring crush

FKBG-API Containerboard (48 times per year)

Mullen burst of linerboard
Concora test of medium

MCCA Color and Appearance (4 times per year)

Gloss at 60°
Color and color difference

CTS Rubber (4 times per year)

Tensile strength, ultimate elongation and tensile stress
Hardness
Mooney viscosity
Vulcanization properties

ASTM Cement (2 times per year)

Chemical (11 chemical components)
Physical (15 characteristics)

AASHTO Bituminous

Asphalt cement (2 times per year)
Cutbacks (once a year)

NBS Collaborative Reference Programs
A05 Technology Building
National Bureau of Standards
Washington, DC 20234


Rev. 10/79

INTRODUCTION

The Collaborative Reference Program for Containerboard is cosponsored by the Fourdrinier Kraft Board Group (FKBG) of the American Paper Institute, Inc. and the National Bureau of Standards. The program is maintained and operated by Collaborative Testing Services, Inc. (CTS). CTS is a non-profit organization of associations that offers CRPs to a wide range of industries.

Samples of three weights of linerboard, nominally 26 lb, 42 lb, and 69 lb and of corrugating medium (26 lb) are separately randomized from uniform narrow rolls and packaged for distribution to the participants. Each month, sufficient test material for four weekly tests is mailed to participants for testing Mullen bursting strength according to TAPPI official testing method T807 os-75 or Concora flat crush strength according to TAPPI official testing method T309 os-71. The participants return their test results to NBS for analysis and receive two monthly reports from NBS. One report is a preliminary individualized report comparing a laboratory's results with the industrial mean. The other is a longer report (as illustrated by this report) showing the data from all participants.

If there are any questions on the notes, the analyses, or the reports in general, contact Jeffrey Horlick on (301) 921-2946 or Thomas L. Cummings on (703) 442-0433.



Jeffrey Horlick, Technical Administrator
NBS Collaborative Reference Programs
Office of Testing Laboratory Evaluation Technology

March 31, 1980

TABLE OF CONTENTS

Page

1	Explanation of Tables
4	Instrument Codes
5	Use of Average Mean as a Reference Standard
6	Bursting Strength, Linerboard 42L1, week 1
8	Bursting Strength, Linerboard 42L3, weeks 2-4
10	Bursting Strength, Linerboard 26K1, weeks 1-4
12	Concora Flat Crush, Corrugating Medium 26D3

EXPLANATION OF TABLES

Each table shows laboratory test results for Mullen bursting strength of linerboard or Concora flat crush strength of corrugating medium. The data are divided into three time spans. On the left of each table is an analysis for each week of the month. In the center is cumulative data for the month and on the right is cumulative data for up to 16 weeks.

Conservative statistical tests have been used in excluding extreme data from the analyses. Thus, where the mean (average) for one laboratory is compared with the average for many laboratories, limits have been used that would exclude only one laboratory in a hundred if all laboratories followed exactly the same testing procedure. Consequently, laboratories receiving "X" flags should review their testing procedures, instrument calibration, and control processes. Similar conservative criteria were used in flagging within-laboratory standard deviations and other statistics.

	LAB	MEANS THIS MONTH			
<u>WEEKLY VALUES:</u>	CODE V	WK-1	WK-2	WK-3	WK-4

LAB CODE - Confidential laboratory identification number known only to the participant and the Collaborative Reference Program staff.

V - Code for indicating instrument type, units used, and any other variation in test procedure or conditions. A '+' in this column means a non-standard variation. Data marked '+' are not included in the combined averages for all laboratories. (see page 4).

MEANS THIS MONTH - For each laboratory each weekly mean is the average of individual test determinations, usually an average of 20 determinations.

FLAGS (following means and standard deviations) -

X - Data excluded from an AV MEAN or average standard deviation because value deviated from the AV MEAN or average standard deviation by more than 2.576 times the appropriate standard deviation. A laboratory following the prescribed test method could obtain such an extreme value by chance only one time in a hundred. Corrective action is almost certainly required.

* - Data included in the CUMULATIVE AV MEAN but the value deviated from this mean by more than 1.960 and less than 2.576 times the SD CUM MEAN. A laboratory following the prescribed test method could obtain such an extreme value by chance only one time in twenty. Corrective action may be desired.

- S - This is a warning to the laboratory but does not affect inclusion or exclusion of the laboratory's results from the corresponding AV MEAN. This flag indicates an extremely high or low within-laboratory standard deviation (SDR, not shown) that could occur by chance only one time in a hundred if the laboratory is following the prescribed test method.
- AV MEAN - (at bottom of table) - The average for the indicated week of the means for all laboratories, except those laboratories marked '+' in column V and those means marked with an 'X'.
- SDR - (not shown) - The standard deviation of within-laboratory measurements; i.e., the Standard Deviation of the Replicate measurements made at one time in one laboratory on one package of test pieces.
- AV SDR - The average for the indicated week of the SDR's of all the laboratories, except those omitted from the AV MEAN. Also an extremely high or low SDR as compared with the AV SDR based on the remaining laboratories is omitted from the AV SDR and the letter 'S' is placed after the laboratory mean for that week. The AV SDR is an index of the within-laboratory precision for repeated measurements; i.e., a measure of the ability of an average laboratory to repeat its results over a short period of time. It includes measurement error and sample variation.
- SD LABS - For each week the standard deviation of the means about the AV MEAN for that week after omitting those means marked with an 'X' or noted '+' in column V. The SD LABS is an index of the among-laboratory precision of the test method as applied by the participating laboratories; i.e., a measure of the ability of laboratories to get comparable results.
- NO. INCL - The number of laboratory means included in the AV MEAN for that week.
- NO. OMIT - The number of laboratory means reported but omitted from AV MEAN because of non-standard equipment, environment or procedure ('+' in column V) or because of extreme results (X following mean).
- NOT RCD - The number of laboratories failing to report data on time or in usable form for this week (but who reported data for at least one of the other weeks of this month), or who received test pieces from a different sample of material and whose data therefore are shown in another table of this report.
- SD SHTS - (Concora only) The average for the indicated week of the among-sheet within-laboratory standard deviations. The SD SHTS is an index primarily of the variability among sheets.

	THIS MONTH		
<u>VALUES THIS MONTH:</u>	MEAN	SDR	SDWKS

- MEAN - The average for the indicated laboratory of the reported weekly MEANS THIS MONTH.
- SDR - The average for the indicated laboratory of the weekly SDRs for the current month.
- SDWKS - For the indicated laboratory, the standard deviation among the laboratory's weekly MEANS THIS MONTH (including those means marked with an 'X').

		CUMULATIVE		
<u>CUMULATIVE VALUES:</u>	MEAN	SDR	SDWKS	WKS

- MEAN - The average for the indicated laboratory of all its weekly means for the number of weeks indicated, including those for the current month. An '*' or 'X' following this CUMULATIVE MEAN indicates the laboratory is running consistently low or high. (See above for explanation of these flags).
- SDR - The average for the indicated laboratory of the weekly SDRs for the indicated number of weeks.
- SDWKS - For the indicated laboratory, the standard deviation among the laboratory's weekly means (including those means marked with an 'X'). SDWKS is an index of the week to week precision; i.e., a measure of the ability of a laboratory to repeat its results from week to week.
- WKS - Number of weeks for which usable results have been reported by that laboratory. At most, 16 weeks of data are included.

	GRAND AVERAGES	
<u>GRAND AVERAGES:</u>	THIS MONTH	CUMULATIVE 12 WEEKS

THIS MONTH - Averages for the four weeks of the quantities shown to the left.

CUMULATIVE - Averages for the indicated number of weeks, including the four weeks of the current month.

AV SDWKS - The average of the SDWKS for all laboratories excluding those marked '+' in column V or with an 'X' following the corresponding THIS MONTH or CUMULATIVE MEAN or SDWKS.

SD CUM MEAN - The larger of either (1) the standard deviation of the CUMULATIVE MEANS about the average CUMULATIVE MEAN after omitting those CUMULATIVE MEANS marked with an 'X' or with a '+' in column V, or (2) the CUMULATIVE SD LABS divided by the square root of the number of weeks cumulated. The former will be appreciably larger than the latter only when there are persistent systematic differences among the laboratories.

INSTRUMENT CODES
FOR
MULLEN BURST OF LINERBOARD
(Column V)

<u>Code</u>	<u>Description</u>
A	Model A, Manual Clamp
H	Model AH, Hydraulic Clamp
I	Model A, Hydraulic Clamp added
J	Jumbo, Hand Clamp, Hand Driven
L	Lhomargy, Hydraulic Clamp, in kPa
M	Model AH, Hydraulic Clamp, Transducer
N	Lhomargy, Hydraulic Clamp, in psi
R	Model A, Air Clamp added
X	Other Model, Please Describe Instrument Make and Model
Y	Nonstandard Instrument or Method
Z	Data received too late to be included in statistical analysis

INSTRUMENT CODES
FOR
CONCORA TEST OF MEDIUM
(Column V)

<u>Code</u>	<u>Description</u>
Z	Data received too late to be included in statistical analysis

Use of Average Mean as a Reference Standard

A large supply of linerboard in three weights was randomized and placed in sealed packages ready for shipment. The supply for each weight of board was divided into several narrow "rolls" or cross-machine "positions" of a larger roll, and each position was separately randomized. Each package contains test pieces from one position only. The position is designated by the number following the letter in the code marked on the package. Thus 42H 1 indicates that this package contains 42 lb board from position 1 of lot H. Samples from the first position are distributed until exhausted, then from the second position, and so forth for each weight of board. Thus for short periods of time (several weeks to months), the samples that the participants test are from the same position of a lot, and for a longer period from the same lot.

The three weights of linerboard distributed in this program may be used as reference standards. The best reference values are the cumulative grand AV MEANS in the latest reports. These values are given at the bottom right of each table. For each weight of board, comparisons should be made first for measurements made on the same position, i.e., for checking your current measurement, use grand AV MEANS that have the same position code as on the packages being tested. The position is shown in the upper left corner of the table. If no report is yet available on the current position, grand AV MEANS from previously tested positions of the same lot may be used as approximate reference values.

Similarly a large supply of a 26 lb corrugating medium was randomized, after dividing into several narrow rolls or positions. The above discussion for linerboard also applies to the corrugating medium.

We are currently using the fourth lot of linerboard and the fourth lot of corrugating medium:

<u>Lot</u>	<u>Material</u>	<u>Codes</u>	<u>Used</u>
1	linerboard	A,B,C	October 1969 - April 1973
2	linerboard	D,E,F	September 1972 - September 1976
3	linerboard	G,H,I,J	October 1976 - September 1979
4	linerboard	K,L,M	September 1979 -
1	corrugating medium	(A)	May 1973 - March 1976
2	corrugating medium	B	April 1976 - February 1977
3	corrugating medium	C	March 1977 - August 1978
4	corrugating medium	D	September 1978 -

COLLABORATIVE REFERENCE PROGRAM
 REPORT NO. 125
 BURSTING STRENGTH (MULLEN), PSI

FEBRUARY 1980

LAB CODE	V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
100	H	114.9				114.9	5.8		114.8	6.5	.8	13
102	H	112.7				112.7	7.3		112.4	7.2	1.9	11
103	I	115.7				115.7	7.9		114.8	5.6	.8	13
105	I	119.5				119.5	7.1		113.0	7.6	3.2	12
106	H	117.2				117.2	7.2		117.6	6.5	1.8	13
108	*Z	121.5				121.5	6.1		117.4	7.6	2.7	5
109	H	118.8				118.8	7.7		114.1	7.4	4.8X	13
110	M	118.5				118.5	8.0		115.4	7.8	1.6	13
111	M	114.3				114.3	7.2		115.2	7.5	1.7	13
112	H	105.8X				105.8X	5.6		110.9*	5.5	2.8	13
113	R	116.1				116.1	7.4		115.9	6.6	.7	13
114	M	115.2				115.2	5.8		116.4	6.8	2.2	12
115	R	117.4				117.4	7.3		117.7	6.0	2.5	13
117	H	112.4				112.4	7.9		111.3*	6.9	1.7	13
119	H	120.2				120.2	7.7		115.1	8.8X	3.3	10
120	R	115.9				115.9	4.9		113.2	7.1	3.8	12
121	M	115.1				115.1	5.9		114.9	7.0	2.6	13
125	I	119.5				119.5	8.8		119.0*	7.4	2.8	13
127	H	114.7				114.7	8.1		115.6	6.8	.7	13
128	H	116.9S				116.9	10.8		115.0	8.0	2.2	13
130	H	116.3				116.3	7.2		116.8	7.6	1.7	13
131	R	112.9				112.9	7.3		111.5	7.2	3.4	13
133	A	114.8				114.8	5.9		115.9	6.6	2.7	12
134	H	113.9				113.9	7.8		117.0	6.6	2.8	12
136	H	113.6				113.6	6.5		112.1	6.7	2.1	13
137	H	120.3				120.3	10.1		120.4X	7.9	3.2	12
138	H	117.3				117.3	6.8		118.2	7.5	1.7	13
139	R	111.0				111.0	7.6		114.0	7.5	5.3X	13
140	H	112.6S				112.6	3.8		112.1	5.2X	1.4	13
141	M	113.5S				113.5	3.6		114.4	5.5	.6	13
142	A	112.9				112.9	5.2		111.1*	5.8	1.6	13
145	H	116.7				116.7	10.1		114.4	7.2	2.3	12
147	H	114.1				114.1	10.0		113.4	7.0	1.9	13
149	H	111.7				111.7	8.8		116.1	7.4	3.6	12
151	H	113.3				113.3	7.5		116.0	7.2	2.4	12
153	H	122.1S				122.1	14.3		115.6	6.0	2.8	13
155	H	119.8				119.8	9.0		116.3	7.5	2.6	13
157	H	110.1				110.1	7.1		116.7	7.1	3.4	13
161	*X	119.3				119.3	8.4		117.3	7.1	3.0	13
165	R	114.1				114.1	6.9		114.2	8.0	1.7	12
167	H	113.5				113.5	7.4		111.8	5.8	1.8	13
169	I	116.6				116.6	4.7		114.3	6.6	2.5	12
171	H	108.8				108.8	7.8		114.0	7.2	2.3	12
172	H	117.0				117.0	5.6		114.0	6.5	1.8	13
173	H	114.0				114.0	6.2		115.6	5.5	1.6	9
174	H	117.1				117.1	6.1		116.4	6.8	2.4	13
175	H	112.0				112.0	9.5		114.3	8.4	2.9	13
176	H	108.3				108.3	7.8		114.1	7.2	2.2	13
177	H	117.9				117.9	6.3		113.9	6.8	3.0	12
182	H	118.6				118.6	5.3		117.2	7.8	2.0	13
184	H	115.8				115.8	7.5		114.9	7.3	2.8	12
186	I	118.1				118.1	7.1		117.2	7.1	2.8	13
188	I	115.1				115.1	6.8		115.4	6.6	1.4	13
198	R	118.8				118.8	6.9		117.7	6.8	1.2	12
274	H	115.4				115.4	6.4		115.9	6.4	.9	9

COLLABORATIVE REFERENCE PROGRAM
 REPORT NO. 125
 BURSTING STRENGTH (MULLEN), PSI

FEBRUARY 1960

TAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
283 H	112.8				112.8	7.0		116.8	6.8	2.4	12
287 A	121.1				121.1	8.7		124.0X	8.6	3.8	13
327 *Z	114.5				114.5	8.4		115.9	8.5	3.2	8
359 H	112.9				112.9	9.1		115.7	7.2	2.4	4
553 M	116.9				116.9	7.0		116.6	7.4	2.2	13
562 A	111.5				111.5	6.6		124.5X	8.0	8.0X	13
568 I	118.9				118.9	8.3		113.0	7.5	3.2	13
569 A	112.8				112.8	9.3		118.9*	7.5	4.3X	11
658 H	115.1				115.1	6.7		115.8	7.7	1.8	13
701 H	118.6				118.6	6.8		116.4	8.2	2.1	13

					GRAND AVERAGES		
					THIS MONTH	CUMULATIVE 13 WEEKS	
	WK-1	WK-2	WK-3	WK-4			
AV MEAN	115.5				AV MEAN	115.5	115.1
AV SDR	7.3				AV SDR	7.3	7.0
SD LABS	3.0				SD LABS	3.0	3.0
NO. INCL	61				NO. INCL	61.0	59.5
NO. OMIT	4				AV SDWKS	6.0	2.2
NET PCD	0				SD CUM MEAN		1.9

LAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
100 H		119.3	118.1	119.8	119.1	7.9	.9	119.1	7.9	.9	3
102 H		114.3	113.7	118.9	115.6	6.7	2.9	115.6	6.7	2.9	3
103 I		120.0	115.5	121.0	118.8	6.3	2.9	118.8	6.3	2.9	3
105 M		120.8	117.2	110.0X	116.0	8.5	5.5	116.0	8.5	5.5X	3
106 H		122.0	121.2	122.3	121.9	6.5	.6	121.9	6.5	.6	3
108 +Z		119.3			119.3	7.8		119.3	7.8		1
109 H		118.1	120.1	120.2	119.5	7.1	1.2	119.5	7.1	1.2	3
110 M		118.5	122.2	120.2	120.3	9.1	1.9	120.3	9.1	1.9	3
111 M		115.7	120.1	118.4	118.1	6.6	2.2	118.1	6.6	2.2	3
112 H		108.7X	107.2X	111.6	109.2X	8.8	2.2	109.2X	8.8	2.2	3
113 R		114.2	115.5	115.1	115.0	6.0	.7	115.0	6.0	.7	3
114 M		117.7	118.4	124.2	120.1	6.4	3.6	120.1	6.4	3.6	3
115 R		109.6	116.2	117.4	114.4	7.4	4.2	114.4	7.4	4.2	3
117 H		115.2	116.5	114.9	115.5	8.0	.9	115.5	8.0	.9	3
119 H		112.3	123.7	117.7	117.9	8.3	5.7	117.9	8.3	5.7X	3
120 R		117.5	116.7	116.8	117.0	7.3	.4	117.0	7.3	.4	3
121 M		117.6	118.6	121.0	119.1	7.9	1.8	119.1	7.9	1.8	3
125 I		119.1	117.7	116.1	117.7	8.5	1.5	117.7	8.5	1.5	3
127 H		122.5	120.9	115.7	119.7	6.4	3.5	119.7	6.4	3.5	3
128 H		118.0	114.1	115.9	116.0	7.0	2.0	116.0	7.0	2.0	3
130 H		119.7	122.6	119.9	120.8	7.5	1.6	120.8	7.5	1.6	3
131 R		115.2	115.6	121.2	117.4	8.4	3.3	117.4	8.4	3.3	3
133 A		115.3	116.0S	115.0	115.4	6.4	.5	115.4	6.4	.5	3
134 H		119.0	116.8	116.0	117.3	7.7	1.5	117.3	7.7	1.5	3
136 H		113.8	118.2	111.5	114.5	7.3	3.4	114.5	7.3	3.4	3
137 H		125.6	121.0	122.5	123.0	7.5	2.3	123.0*	7.5	2.3	3
138 H		123.0	125.3X	121.0	123.1	7.6	2.2	123.1*	7.6	2.2	3
139 R		107.3X		112.9	110.1X	6.5	4.0	110.1X	6.5	4.0	2
140 H			117.5	116.4S	117.0	3.9	.7	117.0	3.9X	.7	2
141 M		114.8	116.1	116.9	115.9	5.8	1.0	115.9	5.8	1.0	3
142 A		116.5	115.8	113.9	115.4	6.9	1.3	115.4	6.9	1.3	3
145 H			113.9	117.6	115.8	6.2	2.6	115.8	6.2	2.6	2
147 H		113.7	117.6	111.5	114.3	6.4	3.1	114.3	6.4	3.1	3
149 H		117.3	116.8	114.7	116.3	6.7	1.4	116.3	6.7	1.4	3
151 H		124.3	119.0	121.0	121.5	6.8	2.7	121.5	6.8	2.7	3
153 H		119.4	122.1	123.0	121.5	7.9	1.8	121.5	7.9	1.8	3
155 H		119.8	120.4	117.7	119.3	8.7	1.4	119.3	8.7	1.4	3
157 H		115.2	114.5	114.2S	114.7	6.0	.5	114.7	6.0	.5	3
161 +X		124.0	122.1		123.0	6.3	1.3	123.0*	6.3	1.3	2
163 H			118.0	119.3	118.7	7.2	.9	118.7	7.2	.9	2
165 R		117.3	116.0	118.5	117.3	5.9	1.3	117.3	5.9	1.3	3
167 H		114.2	118.7	116.8	116.6	8.2	2.2	116.6	8.2	2.2	3
169 I		115.5	115.8	114.3	115.2	6.8	.8	115.2	6.8	.8	3
171 H		116.7	112.9	116.5	115.4	6.5	2.2	115.4	6.5	2.2	3
172 H		116.8	119.5	119.1	118.5	7.5	1.5	118.5	7.5	1.5	3
173 H		127.3X	121.1	119.8	122.7	5.7	4.0	122.7	5.7	4.0	3
174 H		120.6	117.5	119.9	119.3	7.6	1.6	119.3	7.6	1.6	3
175 H		115.1	120.8	121.1	119.0	8.1	3.4	119.0	8.1	3.4	3
176 H		115.1	112.6	120.1	116.0	7.8	3.8	116.0	7.8	3.8	3
177 H		118.7	121.4	119.3	119.8	7.1	1.4	119.8	7.1	1.4	3
182 H		119.4	119.1	124.3	120.9	7.0	2.9	120.9	7.0	2.9	3
184 H		122.8	119.9	122.9	121.9	7.8	1.7	121.9	7.8	1.7	3
186 I		120.2	119.6	121.5	120.5	7.7	.9	120.5	7.7	.9	3
188 H		116.4	116.2	118.9	117.2	6.7	1.5	117.2	6.7	1.5	3
198 R		114.7	113.5	112.9	113.7	6.4	.9	113.7	6.4	.9	3

LAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDP	SDWKS	MEAN	SDR	SDWKS	WKS
250 +N			114.6	116.1S	115.4	9.0	1.1	115.4	9.0	1.1	2
274 H		117.8	116.9	118.2	117.6	7.1	.7	117.6	7.1	.7	3
283 H				120.2	120.2	8.4		120.2	8.4		1
287 A		133.6X	133.0XS	127.5XS	131.4X	11.3	3.3	131.4X	11.3X	3.3	3
327 +Z		121.7	123.3	121.2	122.1	8.4	1.1	122.1	8.4	1.1	3
359 H		112.6	116.7	116.0	115.1	6.1	2.2	115.1	6.1	2.2	3
553 M		122.9	119.9	119.5	120.8	7.1	1.9	120.8	7.1	1.9	3
562 A		122.3	118.0	120.3	120.2	7.5	2.1	120.2	7.5	2.1	3
568 I		123.2	123.1	120.7	122.3	7.3	1.4	122.3	7.3	1.4	3
569 A		122.2	121.6	117.0	120.3	8.0	2.8	120.3	8.0	2.8	3
658 +Z		116.4	116.5		116.5	5.9	.0	116.5	5.9	.0	2
701 H		118.7	118.2	119.9	119.0	7.7	.9	119.0	7.7	.9	3

				GRAND AVERAGES		
	WK-1	WK-2	WK-3	WK-4	THIS MONTH	CUMULATIVE 3 WEEKS
AV MEAN		117.9	118.0	118.2	AV MEAN 118.1	118.1
AV SDR		7.3	7.2	7.4	AV SDR 7.3	7.3
SD LABS		3.4	2.7	3.1	SD LABS 3.1	3.1
NO INCL		54	57	60	NO INCL 57.0	57.0
NO OMIT		8	7	4	AV SDWKS 2.0	1.9
NO PCD		5	3	3	SD CUM MEAN	2.5

LAB CODE	V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
		WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
100	H	81.9	81.2	80.7	82.7	81.6	6.0	.9	80.5	6.0	1.6	12
102	H	80.2	78.8	77.8	75.5	78.1	4.5	2.0	78.4	5.3	1.8	11
103	I	81.0	81.5	78.8	82.0	80.8	5.9	1.4	79.4	5.4	2.0	12
105	M	81.1	79.0	82.2	77.7	80.0	6.8	2.0	81.8	6.3	2.6	12
106	H	78.5	85.6	84.9	81.6	82.7	7.1	3.3	82.4	7.4	2.4	12
108	+Z	84.7	85.8			85.2	6.0	.8	81.3	6.3	3.2	6
109	H	79.9	79.9	80.0	79.1	79.7	6.4	.4	78.2	6.6	2.8	12
110	M	83.6	83.1	84.9	83.8	83.9	6.1	.8	83.4	6.4	1.1	12
111	M	77.2	83.7	76.0	78.5	78.9	7.1	3.4	79.9	6.9	2.2	12
112	H	69.7X	69.8X	72.6XS	69.8X	70.5X	8.2	1.4	71.9X	7.0	1.8	12
113	R	78.9	78.3	78.4	79.1	78.7	4.7	.4	79.7	5.2	1.2	12
114	M	80.6	81.6	86.1	84.3	83.1	6.2	2.5	82.2	6.1	2.3	11
115	R	76.8	77.0	75.7S	76.0	76.4	4.8	.6	78.3	5.5	2.0	12
117	H	80.9	79.2	79.3	78.1	79.4	5.9	1.1	79.4	5.9	2.2	12
119	H	77.4	76.1	81.2	79.4	78.5	6.3	2.3	79.6	6.0	2.1	11
120	R	83.3	82.6	82.0	81.5	82.4	6.8	.8	81.7	6.7	3.4	11
121	M	82.3S	81.1	86.5	85.2	83.8	7.1	2.5	82.9	6.4	2.4	12
125	I	81.9	84.4	79.0	80.1	81.4	6.0	2.4	83.4	5.8	2.8	12
127	H	82.5	81.5	82.8	81.8	82.2	4.8	.6	80.6	5.4	2.0	12
128	H	83.4	79.8	83.8S	82.3	82.3	8.3	1.8	81.1	6.7	1.9	12
130	H	79.6	82.6	82.5	82.4	81.8	7.3	1.4	81.7	7.8	1.9	12
131	R	77.6	77.9	77.9	82.9	79.1	5.8	2.5	80.3	6.6	2.1	12
133	A	78.6	77.9	78.0	77.4	78.0	5.9	.5	80.0	7.0	2.6	12
134	H	82.5	82.1S	80.0	82.0	81.7	6.4	1.1	84.3*	5.9	3.6	12
136	H	79.6	79.9	81.8	82.7	81.0	6.1	1.5	81.1	5.8	1.1	12
137	H	76.5	83.5	77.0S	77.7	78.7	7.9	3.2	78.9	7.1	4.5X	12
138	H	82.6	84.3	85.2	82.5	83.6	7.1	1.3	83.1	7.5	1.9	12
139	R	76.9	74.0S	76.7	75.2	75.7	8.0	1.4	80.8	7.0	6.2X	12
140	H	77.0	75.8S	77.4	74.1	76.1	4.2	1.5	74.8X	4.7X	2.0	12
141	M	78.6	78.7	78.8	78.2	78.6	6.4	.3	78.4	6.1	1.2	12
142	A	77.4	75.6	76.5	77.2	76.7	5.8	.8	75.1X	6.2	1.7	12
145	H	81.7		83.7	81.6	82.4	6.2	1.2	80.9	5.7	2.8	10
147	H	76.5	80.0	81.2	80.8	79.6	6.3	2.1	80.5	7.0	1.8	12
149	H	81.5	83.6	83.1	82.1	82.6	5.9	.9	83.6	6.5	2.0	11
151	H	79.5	79.6	80.4	82.3	80.5	7.7	1.3	78.1	6.0	2.2	11
153	H	85.2	84.1	81.4	81.1	83.0	7.0	2.0	82.9	7.9	1.7	12
155	H	78.0	81.1	78.7	80.2	79.5	5.5	1.4	80.1	6.5	1.1	12
157	H	82.9	79.6	82.5S	83.2	82.0	6.0	1.7	83.7	6.1	3.0	12
161	+X	79.7	79.3S	81.6	84.2	81.2	5.0	2.2	80.5	6.1	2.1	12
163	H			82.1	80.1	81.1	5.3	1.4	79.7	6.3	1.5	9
165	R	84.3	80.9	80.4	82.8	82.1	6.4	1.8	81.6	6.5	1.7	11
167	H	77.2	76.2	79.0	77.5	77.5	5.8	1.2	76.8*	5.5	2.1	12
169	I	82.7	81.5	83.2	81.2	82.1	5.2	1.0	82.8	5.7	1.7	11
171	H	77.8	81.4	78.8	80.5	79.6	6.4	1.6	80.1	6.6	2.1	12
172	H	86.4	80.8	79.3	79.3	81.5	6.0	3.4	78.9	6.0	3.1	12
173	H	82.6	81.0	83.7	82.8	82.5	5.0	1.1	82.0	4.6X	1.5	11
174	H	82.1	84.7	80.2	75.2	80.6	5.8	4.0	81.8	6.3	2.5	12
175	H	77.3	73.5	84.7	85.1	80.2	6.3	5.7	81.5	6.1	4.0X	12
176	H	79.5	79.1	79.7	81.3	79.9	6.7	1.0	79.6	6.6	1.6	12
177	H	80.7	77.4	78.3	76.4	78.2	6.0	1.8	75.8*	6.1	2.5	11
182	H	83.6	85.0	81.5	84.7	83.7	6.0	1.6	83.2	6.6	1.9	12
184	H	79.4	81.4	84.6	82.9	82.1	6.9	2.2	82.0	6.9	2.8	12
186	I	78.8	82.1	80.1	79.5	80.2	5.9	1.4	81.1	5.7	2.7	12
188	I	80.3	80.8	79.9S	80.3	80.3	6.0	.3	80.2	6.0	1.1	12
198	R	89.1X	78.4	78.8	80.4	81.7	5.2	5.0	83.0	6.1	3.4	11

JAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
250 +N			81.1	78.9	80.0	7.9	1.5	73.7X	6.9	4.2X	8
274 H	79.2	80.4	80.3	79.7	79.9	5.6	.5	77.9	5.9	3.0	12
283 H	78.7			79.4	79.0	8.7	.5	80.8	7.6	1.7	10
287 A	86.4	86.8	90.5XS	87.1S	87.7X	8.1	1.9	87.5X	7.7	2.1	12
327 +Z	84.1	84.9	83.3	85.6	84.5	5.5	1.0	85.9X	5.3	2.2	8
359 H	79.6	76.4S	75.5S	75.8	76.8	7.2	1.9	76.8	7.2	1.9	4
553 M	80.4	87.1	87.1	82.4	84.3	6.0	3.4	83.9	6.3	2.8	12
562 A	83.0	81.0	95.5	81.0	82.6	6.2	2.2	84.1	7.2	4.0X	12
568 I		79.5	81.9	83.2	81.6	7.0	1.9	78.6	6.7	2.3	11
569 A	77.9	81.5	80.7	78.5	79.7	6.2	1.7	80.8	6.2	2.6	10
658 +Z	82.3	82.7S	79.4		81.5	5.1	1.8	81.2	5.5	1.9	11
701 H	82.1	81.7	82.7	83.2	82.4	6.7	.6	82.4	7.4	1.6	12

GRAND AVERAGES							
	WK-1	WK-2	WK-3	WK-4	THIS MONTH	CUMULATIVE 12 WEEKS	
AV MEAN	80.4	80.6	80.9	80.6	AV MEAN	80.6	80.5
AV SDR	6.6	6.2	5.9	6.2	AV SDR	6.2	6.2
SD LABS	2.5	3.0	2.9	2.8	SD LABS	2.8	3.3
NO. INCL	58	58	59	61	NO. INCL	59.0	61.7
NO. OMIT	6	5	6	4	AV SDWKS	1.7	2.1
NET RCD	3	4	2	2	SD CUM MEAN		1.9

LAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
100	72.5	71.5	71.5	72.0	71.9	4.5	.5	72.2	4.5	.5	8
102	73.2	73.7	73.7	72.5	73.3	3.6	.6	73.1	3.5	.6	8
105	72.7S	74.7	72.7	74.0	73.6	4.1	1.0	73.5	4.4	.9	6
106	72.3	72.7	72.9	73.0	72.7	3.6	.3	72.8	3.3	.3	8
110	73.9	75.6	76.9	77.1	75.9	3.5	1.5	74.5	3.5	2.0	8
113	72.4	72.1	72.6	71.9	72.3	2.8	.3	72.4	3.0	.4	8
114	71.4	70.7	71.1	72.5	71.4	2.5	.8	71.4	2.6	.8	8
115	72.4	71.7	71.3	73.5	72.2	3.1	1.0	71.9	3.4	1.4	8
119	69.3	72.7	67.1	68.5	69.4	3.5	2.4	69.2	3.5	1.7	7
120	69.8	69.5	70.5	70.5	70.1	3.9	.5	70.6	3.4	.8	8
125	79.3X	78.3	81.0XS	80.8X	79.9X	5.1	1.3	80.1X	5.0X	1.1	8
128	72.4	71.5	72.6	72.0	72.1	3.3	.5	72.3	3.2	.8	8
136	73.5	67.6	70.3	67.6	69.8	3.5	2.8	70.4	3.6	2.0	8
138	76.7	79.2	73.8	79.3	77.3	4.8	2.6	76.7	4.4	2.0	8
140	72.1	72.2	72.4	73.9	72.6	3.2	.8	73.1	3.8	.9	8
151	73.1	73.2	73.1	73.0	73.1	3.8	.1	72.8	3.8	.4	8
161	72.8	68.9	72.7	72.5	71.7	3.9	1.9	73.3	4.7	3.3X	8
164	70.3	72.6	73.8	72.5	72.3	3.7	1.5	72.5	3.8	1.0	8
167	71.6	70.6	70.6	72.9	71.4	3.3	1.1	71.5	3.2	.7	8
177	66.9	70.2	67.8	69.9	68.7	3.3	1.6	69.3	2.9	1.6	8
182	75.9	73.7	70.9	70.7	72.8	3.8	2.5	72.6	4.2	1.7	8
188	72.7	71.8	74.3	71.6	72.6	2.9	1.2	72.0	3.0	1.3	8
198	69.7	69.0	67.8	70.9	69.4	4.1	1.3	70.1	4.0	1.8	8
237	71.4	72.4	72.1	72.5	72.1	3.9	.5	72.4	3.9	.9	8
250			68.2	71.1	69.7	2.2	2.0	68.5	2.0X	1.7	6
269	71.7	71.7	70.3	69.1	70.7	3.5	1.3	71.0	3.5	1.1	8
274	72.8	73.2	72.6	73.2	73.0	3.4	.3	73.0	3.4	.3	4
283	72.7			73.2	72.9	3.2	.4	73.5	3.2	.9	3
284	69.9	71.1	70.2	71.4	70.7	3.5	.7	70.6	3.9	.7	8
287	78.7	75.9	77.5	77.0	77.3	3.7	1.2	77.3*	3.9	.9	8
289	67.9	70.4	68.7	69.8	69.2	3.3	1.1	70.3	3.2	2.3	8
292	67.3	63.2XS	69.5	71.6	67.9	4.0	3.6	68.6	3.6	2.7X	8
350	83.1X	87.2XS	83.3X	84.7X	84.6X	4.7	1.9	83.4X	4.9X	3.6X	8
351	73.8	74.3	73.5	74.5	74.1	3.0	.4	73.8	2.8	.5	8
353	73.2	75.9	75.7		75.0	4.6	1.5	74.8	3.6	1.6	6
355	72.9	72.4	72.2	73.8	72.9	3.9	.7	72.2	3.7	1.1	8
357	69.2	69.2	70.3	69.0	69.5	2.6	.6	69.1	2.9	.9	7
359	81.6X	92.1X	83.3X	87.6X	86.2X	4.7	4.7	85.3X	5.3X	4.3X	7
361	66.5	71.5	71.8	70.1	70.0	3.2	2.4	69.8	3.4	1.7	8
363	71.7	70.8	69.7	67.5	69.9	3.7	1.8	70.3	3.3	1.6	8
365	70.0	69.1	69.1	68.5	69.2	3.9	.6	69.9	3.8	1.7	8
367	75.2	74.0	72.8		74.0	2.6	1.2	74.3	3.2	1.1	6
369	72.8	72.1	71.5	72.5	72.2	3.7	.6	72.6	3.6	.7	8
377	74.3	72.5	75.9	72.7	73.9	3.7	1.6	73.7	3.6	1.3	8
379	74.3	74.9	74.8	73.4	74.4	4.1	.7	74.6	4.4	.7	6
381	73.2	74.2	72.8	72.5	73.2	3.7	.7	72.9	3.7	.7	8
383	73.1	71.0	71.3	73.6	72.2	3.5	1.3	72.3	3.5	1.4	8
385	71.4		71.6	78.9	74.0	2.9	4.3	73.4	3.1	2.9X	7
387	74.4	75.5	78.2	77.1	76.3	4.1	1.7	75.9	3.9	1.3	8
391	62.6X	63.6X		63.6X	63.3X	2.0	.6	67.1*	2.7	4.3X	6
393	75.6	75.9	76.2	78.5	76.6	2.5	1.3	75.5	3.2	1.6	8
395	76.9	75.8	73.2	73.0	74.8	3.7	1.9	74.4	3.6	1.5	8
397	73.3	75.5	73.0	74.9	74.2	3.8	1.2	74.4	3.7	1.5	8
399	68.2	68.4	71.3	72.5	70.1	3.1	2.2	69.9	3.5	1.6	8
553	73.5	73.8	72.6	73.7	73.4	3.7	.5	73.3	3.6	.9	8

LAB CODE V	MEANS THIS MONTH				THIS MONTH			CUMULATIVE			
	WK-1	WK-2	WK-3	WK-4	MEAN	SDR	SDWKS	MEAN	SDR	SDWKS	WKS
562	70.9	70.9	72.8	73.2	72.0	4.1	1.2	71.6	4.0	1.6	8
568	74.3	74.8	73.1	75.7	74.5	3.4	1.1	73.5	3.6	1.5	8
578	81.3XS	78.9	75.3	76.1	77.9	4.7	2.7	76.6	4.1	2.6X	8
609	72.9	73.2	74.0	73.0	73.3	3.9	.5	72.9	3.7	1.1	8
617	76.5	77.5	76.3S	78.9	77.3	4.9	1.2	77.4*	4.7	1.4	8

					GRAND AVERAGES		
	WK-1	WK-2	WK-3	WK-4	THIS MONTH	CUMULATIVE	8 WEEKS
AV MEAN	72.4	72.9	72.4	72.9	AV MEAN	72.6	72.5
AV SDR	3.4	3.5	3.6	3.7	AV SDR	3.5	3.6
SD LABS	2.5	2.7	2.5	2.8	SD LABS	2.6	2.4
NO INCL	54	53	55	54	NO INCL	54.0	54.1
NO OMIT	5	4	3	4	AV SDWKS	1.3	1.2
NOT RCD	1	3	2	2	SD CUM MEAN		2.2
SD SHTS	2.1	2.1	2.2	2.2			

U.S. DEPT. OF COMM. BIBLIOGRAPHIC DATA SHEET	1. PUBLICATION OR REPORT NO. FKBG CRP 125	2. Gov't. Accession No. 	3. Recipient's Accession No.
4. TITLE AND SUBTITLE CONTAINERBOARD Collaborative Reference Program for Containerboard Report #125		5. Publication Date March 31, 1980	
		6. Performing Organization Code 	
7. AUTHOR(S) T.L. Cummings, J. Horlick		8. Performing Organ. Report No. NBSIR 80-1829	
9. PERFORMING ORGANIZATION NAME AND ADDRESS NATIONAL BUREAU OF STANDARDS DEPARTMENT OF COMMERCE WASHINGTON, DC 20234		10. Project/Task/Work Unit No. 	
		11. Contract/Grant No. 	
12. SPONSORING ORGANIZATION NAME AND COMPLETE ADDRESS (Street, City, State, ZIP) Collaborative Testing Services, Inc. 9241 Wood Glade Drive Great Falls, VA 22066; and American Paper Institute/ Fourdrinier Kraft Board Group		13. Type of Report & Period Covered Final	
		14. Sponsoring Agency Code 	
15. SUPPLEMENTARY NOTES ☐ Document describes a computer program; SF-185, FIPS Software Summary, is attached.			
16. ABSTRACT (A 200-word or less factual summary of most significant information. If document includes a significant bibliography or literature survey, mention it here.) Collaborative Reference Programs provide participating laboratories with the means for checking periodically the level and uniformity of their testing in comparison with that of other participating laboratories. An important by-product of the programs is the provision of realistic pictures of the state of the testing art. This is one of the periodic reports showing averages for each participant, within and between laboratory variability, and other information for participants and standards committees.			
17. KEY WORDS (six to twelve entries; alphabetical order; capitalize only the first letter of the first key word unless a proper name; separated by semicolons) Collaborative reference program, Containerboard; Laboratory evaluation; Precision; Reference samples; Testing calibration			
18. AVAILABILITY ☐ Unlimited ☒ For Official Distribution. Do Not Release to NTIS ☐ Order From Sup. of Doc., U.S. Government Printing Office, Washington, DC 20402, SD Stock No. SN003-003- ☐ Order From National Technical Information Service (NTIS), Springfield, VA. 22161		19. SECURITY CLASS (THIS REPORT) UNCLASSIFIED 20. SECURITY CLASS (THIS PAGE) UNCLASSIFIED	21. NO. OF PRINTED PAGES 17 22. Price

