

NATIONAL BUREAU OF STANDARDS REPORT

4449

**Analysis of Mercury Lamps and Filter Combinations
for Use as Aviation-Green Lights**



**U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS**

U. S. DEPARTMENT OF COMMERCE

Sinclair Weeks, *Secretary*

NATIONAL BUREAU OF STANDARDS

A. V. Astin, *Director*



THE NATIONAL BUREAU OF STANDARDS

The scope of activities of the National Bureau of Standards is suggested in the following listing of the divisions and sections engaged in technical work. In general, each section is engaged in specialized research, development, and engineering in the field indicated by its title. A brief description of the activities, and of the resultant reports and publications, appears on the inside of the back cover of this report.

Electricity and Electronics. Resistance and Reactance. Electron Tubes. Electrical Instruments. Magnetic Measurements. Process Technology. Engineering Electronics. Electronic Instrumentation. Electrochemistry.

Optics and Metrology. Photometry and Colorimetry. Optical Instruments. Photographic Technology. Length. Engineering Metrology.

Heat and Power. Temperature Measurements. Thermodynamics. Cryogenic Physics. Engines and Lubrication. Engine Fuels.

Atomic and Radiation Physics. Spectroscopy. Radiometry. Mass Spectrometry. Solid State Physics. Electron Physics. Atomic Physics. Nuclear Physics. Radioactivity. X-rays. Betatron. Nucleonic Instrumentation. Radiological Equipment. AEC Radiation Instruments.

Chemistry. Organic Coatings. Surface Chemistry. Organic Chemistry. Analytical Chemistry. Inorganic Chemistry. Electrodeposition. Gas Chemistry. Physical Chemistry. Thermochemistry. Spectrochemistry. Pure Substances.

Mechanics. Sound. Mechanical Instruments. Fluid Mechanics. Engineering Mechanics. Mass and Scale. Capacity, Density, and Fluid Meters. Combustion Controls.

Organic and Fibrous Materials. Rubber. Textiles. Paper. Leather. Testing and Specifications. Polymer Structure. Organic Plastics. Dental Research.

Metallurgy. Thermal Metallurgy. Chemical Metallurgy. Mechanical Metallurgy. Corrosion. Mineral Products. Porcelain and Pottery. Glass. Refractories. Enameled Metals. Concreting Materials. Constitution and Microstructure.

Building Technology. Structural Engineering. Fire Protection. Heating and Air Conditioning. Floor, Roof, and Wall Coverings. Codes and Specifications.

Applied Mathematics. Numerical Analysis. Computation. Statistical Engineering. Mathematical Physics.

Data Processing Systems. Components and Techniques. Digital Circuitry. Digital Systems. Analogue Systems.

Cryogenic Engineering. Cryogenic Equipment. Cryogenic Processes. Properties of Materials. Gas Liquefaction.

Radio Propagation Physics. Upper Atmosphere Research. Ionospheric Research. Regular Propagation Services.

Radio Propagation Engineering. Frequency Utilization Research. Tropospheric Propagation Research.

Radio Standards. High Frequency Standards. Microwave Standards.

● Office of Basic Instrumentation

● Office of Weights and Measures

NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT
0201-20-2331

December 21, 1955

NBS REPORT
4449

Analysis of Mercury Lamps and Filter Combinations
for Use as Aviation-Green Lights

by
I. Nimeroff

Prepared for
Equipment Laboratory
Wright Air Development Center
Department of the Air Force



U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

The publication, reprinting,
or otherwise using the
information contained herein
without permission is ob-
ject to the provisions of
Title 17, U.S.C. Such permis-
sion is not necessary if the
information is prepared by
the author and is not
otherwise published.

Approved for public release by the
director of the National Institute of
Standards and Technology (NIST)
on October 9, 2015

Part, is prohibited
without permission of
the National Bureau of
Standards, Washington
D.C. It has been speci-
fically prepared for its own use.

Analysis of Mercury Lamps and Filter Combinations for Use as Aviation-Green Lights

1. PURPOSE OF ANALYSIS

The purpose of this analysis is to compute the luminous transmittance and chromaticity coordinates of present aviation-green filters (designed for use with incandescent lamps) when they are used in combination with currently available mercury lamps. Should these combinations fail to meet either the present or proposed aviation-green light specification, suitable filters would then be designed.

2. MERCURY LAMPS

The energy radiated in the visible region by mercury lamps consists of spectral lines and a continuum. The spectral-emittance data for mercury lamps used in this analysis were obtained from General Electric Company's brochure LS-103, June 1955. The performance of the following lamp types was analyzed: H250-A5, BH6, H400-E1 and H1000-A15. The relative spectral-emittance data for these lamps are shown in figure 1.

The luminous efficiency index of each of these lamps and of an incandescent lamp operated at 2854°K, listed in table I, indicates that the mercury lamps are relatively efficient in the production of visible radiant energy. The luminous-efficiency index of a lamp is defined as:

$$100 \frac{\int_{380}^{760} P_{\lambda} \bar{y}_{\lambda} d\lambda}{\int_{380}^{760} P_{\lambda} d\lambda}$$

where P_{λ} is the spectral radiant flux and \bar{y}_{λ} is the CIE relative luminous-efficiency function.

Also listed in table I are the chromaticities of mercury lamps, H250-A5 and BH6 and of an incandescent lamp operating at 2854°K. The chromaticity coordinates of these lamps are plotted

on figure 2. Detailed analysis of the H250-A5 lamp was undertaken because its spectral distribution closely resembles that for H400-E1 and H1000-A15. Detailed analysis of the BH6 lamp was undertaken because this lamp differs from the others by having a higher spectral continuum.

Table I
Chromaticity, Luminous-Efficiency Index, and Efficiency
of Mercury and Incandescent Lamps

Lamp Type	Chromaticity Coordinates			Luminous- Efficiency Index	Efficiency (Rated Lumens per Watt)
	x	y	z		
H250-A5	0.318	0.379	0.303	54	44
BH6	.277	.330	.393	40	65
H400-E1	--	--	--	55	50
H1000-A15	--	--	--	55	52
Incandescent	.448	.408	.144	25	20

2.1 Performance of Mercury Lamps with Conventional Aviation-Green Filters.

In computing the performance of the lamps with aviation-green filters, spectral transmittance data, T_λ , for the transmittance standard, WF590, were used. Luminous transmittance, T , of this filter was computed for an incandescent tungsten lamp operated at 2854°K as well as for the mercury lamps. Chromaticity coordinates, x , y , and z , and luminous transmittance were computed for the H250-A5 and BH6 mercury lamps and the incandescent lamp. These computed results are listed in table II. The chromaticity coordinates are plotted on figure 2.

Table II
Luminous Transmittance and Chromaticity Coordinates
of Lamp and Aviation-Green Filter Combinations

Lamp Type	Chromaticity Coordinates			T (percent)
	x	y	z	
H250-A5	0.232	0.276	0.492	22
BH6	.192	.249	.559	27
H400-E1	--	--	--	21
H1000-A15	--	--	--	22
Incandescent	.205	.400	.395	20

The colors of the combination of the aviation-green filter and the mercury lamps are obviously too blue for use as aviation-green lights. The mercury lamps provide little increase in luminous transmittance over the incandescent lamp.

3. DESIGN OF FILTERS FOR MERCURY LAMPS TO YIELD AVIATION-GREEN LIGHT

If the radiant energy emitted by the mercury lamp in the visible region of the spectrum were composed entirely of spectral lines 404.7, 435.8, 546.1, and 578.0 m μ , the color of any mercury lamp-filter combination would lie within a chromaticity region defined by these spectral lines. This chromaticity region is shown by dashes on figure 2. If we wish to obtain a color that will lie in the aviation-green chromaticity region, a filter is required that will almost completely absorb the energy of line 578.0 m μ and will partially absorb the energy of lines 404.7 and 435.8 m μ .

As no single filter known can satisfy these requirements, two-component filter combinations of Didymium and Noviol filters were tried. Didymium filters have an absorption band in the region of 578 m μ and Noviol filters absorb energy in the blue and violet regions of the spectrum.

The design data for the two combinations that show promise of usefulness are listed in table III. The thickness of each filter component is designed on the basis of spectral data published in Glass Color Filters, Corning, 1948, for stock thickness t_0 .

Table III

Filter Design Data

Filter Designation	Corning Ident. No.	Relative Thickness	Name
A	1-63	0.4 t_0	Didymium
	3-72	0.5 t_0	Noviol B
B	1-63	1.0 t_0	Didymium
	3-73	1.0 t_0	Noviol A

Figure 3 shows the computed spectral transmittance of the components and the combination of designed filter A. Figure 4 shows the computed spectral transmittance of the components and

the combination of designed filter B. The location of each mercury spectral line is indicated by an arrow on figures 3 and 4.

The chromaticity coordinates and luminous transmittance of filters A and B in combination with lamps H250-A5 and BH6 were computed. The results of these computations are listed in table IV. The chromaticity coordinates are plotted on figure 2.

Table IV

Chromaticity Coordinates and Luminous Transmittance
of Mercury Lamps and Designed Filter Combinations


Filter Designation	Lamp Type	Chromaticity Coordinates			Luminous Transmittance (percent)
		x	y	z	
A	H250-A5	0.356	0.587	0.057	60
A	BH6	.313	.522	.165	66
B	H250-A5	.273	.425	.302	48
B	BH6	.267	.376	.358	56

4. DISCUSSION

The chromaticity coordinates for mercury lights show that the color of each light lies on the green side of the Planckian Locus near 6000°K. The chromaticity of the mercury lamps in combination with the present aviation-green filter indicates that the resulting color is too blue for aviation green. The H250-A5 lamp in combination with designed filter B and the BH6 lamp in combination with designed filter A satisfy the proposed aviation green limits. Designed filter A shifts the color of mercury lamps toward yellow-green, while designed filter B shifts the color of the mercury lamp toward green.

The mercury lines plotted as points on the spectrum locus of figure 2 serve to define approximately the chromaticity region within which chromaticities of mercury lamp-filter combinations will lie. The BH6 lamp in combination with the present aviation-green filter falls just outside of this region because of the high spectral continuum in the spectral region of 490 mμ.

The chromaticity region defined by the mercury lines indicates that use of mercury lamps is theoretically possible for lunar white,



aviation blue, and aviation green. For lunar white, line 546 mμ needs to be eliminated. For aviation blue, lines 546 mμ and 578 mμ need to be greatly reduced. For aviation green, line 578 mμ needs to be eliminated, and lines 405 mμ and 436 mμ reduced.

In the use of mercury lamps, precaution should be taken to dissipate the heat produced by the ultraviolet radiation that will be absorbed by the filter. The absorbed radiation might heat the filter to the cracking point. Incandescent lamps emit very little ultraviolet radiant energy but have much infrared. The filters in use with incandescent lamps generally transmit the infrared so no special precautions need be taken.

SPECTRAL CHARACTERISTICS OF MERCURY LAMPS




Figure 1




Figure 2
 NBS
 I Equal Energy




Figure 3




Figure 4

THE NATIONAL BUREAU OF STANDARDS

Functions and Activities

The functions of the National Bureau of Standards are set forth in the Act of Congress, March 3, 1901, as amended by Congress in Public Law 619, 1950. These include the development and maintenance of the national standards of measurement and the provision of means and methods for making measurements consistent with these standards; the determination of physical constants and properties of materials; the development of methods and instruments for testing materials, devices, and structures; advisory services to Government Agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; and the development of standard practices, codes, and specifications. The work includes basic and applied research, development, engineering, instrumentation, testing, evaluation, calibration services, and various consultation and information services. A major portion of the Bureau's work is performed for other Government Agencies, particularly the Department of Defense and the Atomic Energy Commission. The scope of activities is suggested by the listing of divisions and sections on the inside of the front cover.

Reports and Publications

The results of the Bureau's work take the form of either actual equipment and devices or published papers and reports. Reports are issued to the sponsoring agency of a particular project or program. Published papers appear either in the Bureau's own series of publications or in the journals of professional and scientific societies. The Bureau itself publishes three monthly periodicals, available from the Government Printing Office: The Journal of Research, which presents complete papers reporting technical investigations; the Technical News Bulletin, which presents summary and preliminary reports on work in progress; and Basic Radio Propagation Predictions, which provides data for determining the best frequencies to use for radio communications throughout the world. There are also five series of nonperiodical publications: The Applied Mathematics Series, Circulars, Handbooks, Building Materials and Structures Reports, and Miscellaneous Publications.

Information on the Bureau's publications can be found in NBS Circular 460, Publications of the National Bureau of Standards (\$1.25) and its Supplement (\$0.75), available from the Superintendent of Documents, Government Printing Office. Inquiries regarding the Bureau's reports and publications should be addressed to the Office of Scientific Publications, National Bureau of Standards, Washington 25, D. C.

